This is a preview - click here to buy the full publication

IEC 60793-1-31

Edition 2.0 2010-05

INTERNATIONAL STANDARD

withdrawn

Optical fibres –
Part 1-31: Measurement methods and test procedures – Tensile strength

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE S

ICS 33.180.10

ISBN 978-2-88910-916-6

® Registered trademark of the International Electrotechnical Commission

This is a preview - click here to buy the full publication

CONTENTS

FOREWORD 4
INTRODUCTION 6
1 Scope 7
2 Normative references 7
3 Apparatus 7
3.1 General 7
3.2 Gripping the fibre at both ends 8
3.3 Sample support 8
3.4 Stretching the fibre 8
3.5 Measuring the force at failure 9
3.6 Environmental control equipment 9
4 Sample preparation 9
4.1 Definition 9
4.2 Sample size and gauge length 9
4.3 Auxiliary measurements 10
4.4 Environment 11
5 Procedure 11
5.1 Preliminary steps 11
5.2 Procedure for a single specimen 11
5.3 Procedure for completing all samples for a given nominal strain rate 11
6 Calculations 12
6.1 Conversion of tensile load to failure stress 12
6.2 Preparation of a Weibull plot 13
6.3 Computation of Weibull parameters 13
7 Results 14
7.1 The following information should be reported for each test: 14
7.2 The following information should be provided for each test: 14
8 Specification information 14
Annex A (informative) Typical dynamic testing apparatus 15
Annex B (informative) Guideline on gripping the fibre 17
Annex C (informative) Guideline on stress rate 21
Bibliography 22

Figure 1 – Bimodal tensile strength Weibull plot for a 20 m gauge length test set-up at 5 %/min strain rate 10
Figure A.1 – Capstan design 15
Figure A.2 – Translation test apparatus 15
Figure A.3 – Rotating capstan apparatus 16
Figure A.4 – Rotating capstan apparatus for long lengths 16
Figure B.1 – Gradual slippage 17
Figure B.2 – Irregular slippage 17
Figure B.3 – Sawtooth slippage 18
Figure B.4 – Acceptable transfer function 18
Figure B.5 – Typical capstan 19

Withdrawn

This is a preview - click here to buy the full publication

Figure B.6 – Isostatic compression 19
Figure B.7 – Escargot wrap 20
Figure C.1 – System to control stress rate 21
Figure C.2 – Time variation of load and loading speed 21

Withdrawn

This is a preview - click here to buy the full publication

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 1-31: Measurement methods and test procedures – Tensile strength

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-31 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This second edition cancels and replaces the first edition published in 2001. This edition constitutes a technical revision.

The main change with respect to the previous edition is the addition of comprehensive details, such as examples of fibre clamping as given in Annexes A, B and C.

Withdrawn

This is a preview - click here to buy the full publication

The text of this standard is based on the following documents:

CDV	Report on voting
86A/1285/CDV	86A/1308/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60793-1series, published under the general title *Optical fibres – Measurement methods and test procedures*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

Withdrawn

This is a preview - click here to buy the full publication

INTRODUCTION

Failure stress distributions can be used to predict fibre reliability in different conditions. IEC/TR 62048 shows mathematically how this can be done. To complete a given reliability projection, the tests used to characterize a distribution shall be controlled for the following:

- Population of fibre, e.g., coating, manufacturing period, diameter
- Gauge length, i.e., length of section that is tested
- Stress or strain rates
- Testing environment
- Preconditioning or aging treatments
- Sample size

This method measures the strength of optical fibre at a specified constant strain rate. It is a destructive test, and is not a substitute for prooftesting.

This method is used for those *typical* optical fibres for which the median fracture stress is greater than 3,1 GPa (450 kpsi) in 0,5 m gauge lengths at the highest specified strain rate of 25 %/min. For fibres with lower median fracture stress, the conditions herein have not demonstrated sufficient precision.

Typical testing is conducted on “short lengths”, up to 1 m, or on “long lengths”, from 10 m to 20 m with sample size ranging from 15 to 30.

The test environment and any preconditioning or aging is critical to the outcome of this test. There is no agreed upon model for extrapolating the results for one environment to another environment. For failure stress at a given stress or strain rate, however, as the relative humidity increases, failure stress decreases. Both increases and decreases in the measured strength distribution parameters have been observed as the result of preconditioning at elevated temperature and humidity for even a day or two.

This test is based on the theory of fracture mechanics of brittle materials and on the power-law description of flaw growth (see IEC TR 62048). Although other theories have been described elsewhere, the fracture mechanics/power-law theory is the most generally accepted.

A typical population consists of fibre that has not been deliberately damaged or environmentally aged. A typical fibre has a nominal diameter of 125 µm, with a 250 µm or less nominal diameter acrylate coating. Default conditions are given for such typical populations. Atypical populations might include alternative coatings, environmentally aged fibre, or deliberately damaged or abraded fibre. Guidance for atypical populations is also provided.

Withdrawn

This is a preview - click here to buy the full publication

OPTICAL FIBRES –

Part 1-31: Measurement methods and test procedures – Tensile strength

1 Scope

This part of IEC 60793 provides values of the tensile strength of optical fibre samples and establishes uniform requirements for the mechanical characteristic – tensile strength. The method tests individual lengths of uncabled and unbundled glass optical fibre. Sections of fibre are broken with controlled increasing stress or strain that is uniform over the entire fibre length and cross section. The stress or strain is increased at a nominally constant rate until breakage occurs.

The distribution of the tensile strength values of a given fibre strongly depends on the sample length, loading velocity and environmental conditions. The test can be used for inspection where statistical data on fibre strength is required. Results are reported by means of statistical quality control distribution. Normally the test is carried out after temperature and humidity conditioning of the sample. However, in some cases, it may be sufficient to measure the values at ambient temperature and humidity conditions

This method is applicable to types A1, A2, A3, B and C optical fibres.

Warning – This test involves stretching sections of optical fibre until breakage occurs. Upon breakage, glass fragments can be distributed in the test area. Protective screens are recommended. Safety glasses should be worn at all times in the testing area.

2 Normative references

The following referenced documents are indispensable for the application of this document.

For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

Withdrawn