

INTERNATIONAL STANDARD

IEC 60216-3

Second edition
2006-04

Electrical insulating materials – Thermal endurance properties –

Part 3: Instructions for calculating thermal endurance characteristics

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland
Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale
International Electrotechnical Commission
Международная Электротехническая Комиссия

PRICE CODE

X

For price, see current catalogue

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms, definitions, symbols and abbreviated terms.....	6
4 Principles of calculations	10
4.1 General principles	10
4.2 Preliminary calculations.....	10
4.3 Variance calculations	11
4.4 Statistical tests.....	12
4.5 Results.....	12
5 Requirements and recommendations for valid calculations	13
5.1 Requirements for experimental data	13
5.2 Precision of calculations.....	13
6 Calculation procedures.....	13
6.1 Preliminary calculations.....	13
6.2 Main calculations.....	17
6.3 Statistical tests.....	19
6.4 Thermal endurance graph	21
7 Calculation and requirements for results.....	21
7.1 Calculation of thermal endurance characteristics.....	21
7.2 Summary of statistical tests and reporting	22
7.3 Reporting of results.....	22
8 Test report.....	22
Annex A (normative) Decision flow chart.....	24
Annex B (normative) Decision table	25
Annex C (informative) Statistical tables.....	26
Annex D (informative) Worked examples	35
Annex E (informative) Computer program	42
Bibliography.....	50
Figure D.1 – Thermal endurance graph.....	39
Figure D.2 – Example 3: Property-time graph (destructive test data).....	41
Table B.1 – Decisions and actions according to tests.....	25
Table C.1 – Coefficients for censored data calculations	26
Table C.2 – Fractiles of the F -distribution, $F(0,95, f_n, f_d)$	32
Table C.3 – Fractiles of the F -distribution, $F(0,995, f_n, f_d)$	33
Table C.4 – Fractiles of the t -distribution, $t_{0,95}$	34
Table C.5 – Fractiles of the χ^2 -distribution.....	34

Table D.1 – Worked example 1 – Censored data (proof tests).....	35
Table D.2 – Worked example 2 – Complete data (non-destructive tests).....	37
Table D.3 – Worked example 3 – Destructive tests	40
Table E.1 – Non-destructive test data	43
Table E.2 – Destructive test data	44

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 3: Instructions for calculating thermal endurance characteristics

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60216-3 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems¹.

This second edition of IEC 60216-3 cancels and replaces the first edition, published in 2002, and constitutes a technical revision.

The major technical changes with regard to the first edition concern an updating of Table C.2. In addition, the scope has been extended to cover a greater range of data characteristics, particularly with regard to incomplete data, as often obtained from proof test criteria. The greater flexibility of use should lead to more efficient employment of the time available for ageing purposes. Finally, the procedures specified in this part of IEC 60216 have been extensively tested and have been used to calculate results from a large body of experimental data obtained in accordance with other parts of the standard. Annex E “Computer program” has been completely reworked.

¹ Provisional title: IEC technical committee 112 has been formed out of a merger between subcommittee 15E and technical committee 98.

The text of this standard is based on the following documents:

FDIS	Report on voting
112/26/FDIS	112/29/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 60216 consists of the following parts, under the general title *Electrical insulating materials – Thermal endurance properties*²:

- Part 1: Ageing procedures and evaluation of test results
- Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria
- Part 3: Instructions for calculating thermal endurance characteristics
- Part 4: Ageing ovens
- Part 5: Determination of relative thermal endurance index (RTE) of an insulating material
- Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method

NOTE This series may be extended. For revisions and new parts, see the current catalogue of IEC publications for an up-to-date list.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A CD-ROM containing the computer program and data files referred to in Annex E is affixed to the back cover of this publication.

A bilingual version of this publication may be issued at a later date.

The contents of the corrigendum of December 2009 have been included in this copy.

² Titles of existing parts in this series will be updated at the time of their next revision.

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 3: Instructions for calculating thermal endurance characteristics

1 Scope

This part of IEC 60216 specifies the calculation procedures to be used for deriving thermal endurance characteristics from experimental data obtained in accordance with the instructions of IEC 60216-1 and IEC 60216-2, using fixed ageing temperatures and variable ageing times.

The experimental data may be obtained using non-destructive, destructive or proof tests. Data obtained from non-destructive or proof tests may be incomplete, in that measurement of times taken to reach the endpoint may have been terminated at some point after the median time but before all specimens have reached end-point.

The procedures are illustrated by worked examples, and suitable computer programs are recommended to facilitate the calculations.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60216-1:2001, *Electrical insulating materials – Properties of thermal endurance – Part 1: Ageing procedures and evaluation of test results*

IEC 60216-2:2005, *Electrical insulating materials – Properties of thermal endurance – Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria*

IEC 60493-1:1974, *Guide for the statistical analysis of ageing test data – Part 1: Methods based on mean values of normally distributed test results*