



INTERNATIONAL STANDARD

**Magnetic materials –
Part 10: Methods of measurement of magnetic properties of electrical steel strip
and sheet at medium frequencies**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.030

ISBN 978-2-8322-3672-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 General principle of a.c. measurements.....	8
4.1 General.....	8
4.2 Principle of the 25 cm Epstein frame method	8
4.3 Test specimen	8
4.4 The 25 cm Epstein frame	9
4.5 Air flux compensation.....	10
4.6 Power supply	11
4.7 Voltage measurement	11
4.7.1 General	11
4.7.2 Average type voltmeter	11
4.7.3 RMS voltmeter.....	11
4.8 Current measurement	12
4.9 Frequency measurement.....	12
4.10 Power measurement	12
5 Procedure for the determination of the specific total loss	12
5.1 General.....	12
5.2 Preparation for measurement.....	12
5.3 Adjustment of power supply	13
5.4 Measurements of power	14
5.5 Determination of the specific total loss	14
5.6 Reproducibility of the specific total loss measurement	15
6 Procedure for the determination of the peak value of magnetic polarization, r.m.s. value of magnetic field strength, peak value of magnetic field strength and specific apparent power	15
6.1 General.....	15
6.2 Test specimen	15
6.3 Principle of measurement.....	15
6.3.1 Peak value of magnetic polarization \hat{J}	15
6.3.2 RMS value of the magnetizing current (of the magnetic field strength).....	16
6.3.3 Peak value of magnetic field strength	16
6.4 Apparatus	17
6.4.1 Average rectified voltage measurement	17
6.4.2 Current measurement	17
6.4.3 Peak current measurement.....	17
6.4.4 Resistor R_n	18
6.4.5 Mutual inductor M_D	18
6.5 Measuring procedure	18
6.6 Determination of the peak value of magnetic polarization \hat{J}	18
6.7 Determination of the r.m.s. value of magnetic field strength \tilde{H}	19
6.8 Determination of the peak value of magnetic field strength \hat{H}	19

6.9	Determination of the specific apparent power S_S	20
6.10	Reproducibility	21
7	Test report.....	21
Annex A (informative)	Epstein frame for use at medium frequencies	22
Annex B (informative)	Digital sampling method for the determination of the magnetic properties	23
B.1	General.....	23
B.2	Technical details and requirements	23
B.3	Calibration aspects	25
B.4	Numerical air flux compensation	26
Bibliography	27
Figure 1	– Double-lapped joints	8
Figure 2	– The 25 cm Epstein frame	9
Figure 3	– Circuit for the wattmeter method	13
Figure 4	– Circuit for measuring r.m.s. value of the magnetizing current	16
Figure 5	– Circuit for measuring the peak value of magnetic field strength using a peak voltmeter	16
Figure 6	– Circuit for measuring the peak value of magnetic field strength using a mutual inductor M	17

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MAGNETIC MATERIALS –

Part 10: Methods of measurement of magnetic properties of electrical steel strip and sheet at medium frequencies

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-10 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

This second edition cancels and replaces the first edition published in 1988. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) adaption to modern measurement and evaluation methods, in particular the introduction of the widely spread digital sampling method for the acquisition and evaluation of the measured data;
- b) introduction of formal changes which adapt this standard to other standards of the 60404 series;
- c) revision of the problem of the air flux compensation taking account of the condition of the higher frequencies;

- d) revision of the capacitive coupling of mutual inductor windings together with the consideration of the alternative method of numerical air flux compensation.

The text of this standard is based on the following documents:

CDV	Report of voting
68/523/CDV	68/556/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60404 series, published under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

The contents of the corrigendum of March 2018 have been included in this copy.

INTRODUCTION

Besides the fact that the first edition of this part of IEC 60404 is more than 25 years old, the main purpose of this revision is to adapt it to modern measurement and evaluation methods, in particular to introduce the widely spread digital sampling method for the acquisition and evaluation of the measured data.

In addition, the problem of the air flux compensation had to be re-considered under the condition of the elevated frequencies. Capacitive coupling of mutual inductor windings require observance of significant phase shift influence and suggest consideration of the alternative method of numerical air flux compensation. An increase of the frequency range to 20 kHz was discussed by TC 68 since some manufacturers of electrical steel include this range in their catalogues. However, TC 68 decided to keep the frequency range to that defined in IEC 60404-10:1988: 400 Hz to 10 kHz.

MAGNETIC MATERIALS –

Part 10: Methods of measurement of magnetic properties of electrical steel strip and sheet at medium frequencies

1 Scope

This part of IEC 60404 is applicable to grain-oriented and non-oriented electrical steel strip and sheet for measurements of a.c. magnetic properties in the frequency range 400 Hz to 10 000 Hz.

The object of this document is to define the general principles and the technical details of the measurement of magnetic properties of electrical steel strip and sheet by means of an Epstein frame.

The Epstein frame is applicable to test specimens obtained from electrical steel strips and sheets of any grade. The AC magnetic characteristics are determined for sinusoidal induced voltages, for specified peak values of magnetic polarization and for a specified frequency.

The measurements are to be made at an ambient temperature of $(23 \pm 5)^\circ\text{C}$ on test specimens which have first been demagnetized.

NOTE Throughout this document the term "magnetic polarization" is used as defined in IEC 60050-221. In some standards of the IEC 60404 series, the term "magnetic flux density" was used.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-121, *International Electrotechnical Vocabulary – Part 121: Electromagnetism*

IEC 60050-221, *International Electrotechnical Vocabulary – Chapter 221: Magnetic materials and components*

IEC 60404-8 (all parts), *Magnetic materials – Part 8: Specifications for individual materials*

IEC 60404-13, *Magnetic materials – Part 13: Methods of measurement of density, resistivity and stacking factor of electrical steel sheet and strip*