



IEC 60502-2

Edition 3.1 2024-05
CONSOLIDATED VERSION

INTERNATIONAL STANDARD



**Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV) –
Part 2: Cables for rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.060.20

ISBN 978-2-8322-9033-0

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	11
1 Scope.....	13
2 Normative references	13
3 Terms and definitions	15
3.1 Definitions of dimensional values (thicknesses, cross-sections, etc.)	15
3.2 Definitions concerning the tests	16
4 Voltage designations and materials	16
4.1 Rated voltages.....	16
4.2 Insulating compounds	17
4.3 Sheathing compounds.....	18
5 Conductors.....	19
6 Insulation.....	19
6.1 Material	19
6.2 Insulation thickness	19
7 Screening.....	20
7.1 General.....	20
7.2 Conductor screen.....	20
7.3 Insulation screen	20
8 Assembly of three-core cables, inner coverings and fillers	21
8.1 General.....	21
8.2 Inner coverings and fillers	21
8.2.1 Construction	21
8.2.2 Material	21
8.2.3 Thickness of extruded inner covering.....	21
8.2.4 Thickness of lapped inner covering.....	21
8.3 Cables having a collective metal layer (see Clause 9).....	22
8.4 Cables having a metal layer over each individual core (see Clause 10).....	22
9 Metal layers for single-core and three-core cables.....	22
10 Metal screen.....	22
10.1 Construction	22
10.2 Requirements	23
10.3 Metal screens not associated with semi-conducting layers	23
11 Concentric conductor.....	23
11.1 Construction	23
11.2 Requirements	23
11.3 Application.....	23
12 Metal sheath.....	23
12.1 Lead sheath.....	23
12.2 Other metal sheaths.....	23
13 Metal armour.....	24
13.1 Types of metal armour	24
13.2 Materials.....	24
13.3 Application of armour	24
13.3.1 Single-core cables.....	24
13.3.2 Three-core cables.....	24

13.3.3	Separation sheath	24
13.3.4	Lapped bedding under armour for lead sheathed cables	25
13.4	Dimensions of the armour wires, and armour tapes and armour strips	25
13.5	Correlation between cable diameters and armour dimensions	25
13.6	Round or flat wire armour	26
13.7	Double tape armour	26
13.8	Interlock metal tape armour	27
14	Oversheath	27
14.1	General	27
14.2	Material	27
14.3	Thickness	28
15	Test conditions	28
15.1	Ambient temperature	28
15.2	Frequency and waveform of power frequency test voltages	28
15.3	Waveform of impulse test voltages	28
15.4	Determination of the cable conductor temperature	28
16	Routine tests	29
16.1	General	29
16.2	Electrical resistance of conductors	29
16.3	Partial discharge test	29
16.4	Voltage test	29
16.4.1	General	29
16.4.2	Test procedure for single-core cables	30
16.4.3	Test procedure for three-core cables	30
16.4.4	Test voltage	30
16.4.5	Requirement	30
16.5	Electrical test on oversheath of the cable	30
17	Sample tests	30
17.1	General	30
17.2	Frequency of sample tests	31
17.2.1	Conductor examination and check of dimensions	31
17.2.2	Electrical and physical tests	31
17.3	Repetition of tests	31
17.4	Conductor examination	31
17.5	Measurement of thickness of insulation and of non-metal sheaths (including extruded separation sheaths, but excluding inner extruded coverings)	31
17.5.1	General	31
17.5.2	Requirements for the insulation	31
17.5.3	Requirements for the non-metal sheaths	32
17.6	Measurement of thickness of lead sheath	32
17.6.1	General	32
17.6.2	Strip method	32
17.6.3	Ring method	32
17.7	Measurement of armour wires, and tapes and armour strips	33
17.7.1	Measurement on wires	33
17.7.2	Measurement on tapes and armour strips	33
17.7.3	Requirements	33

17.8	Measurement of external diameter	33
17.9	Voltage test for 4 h	33
17.9.1	Sampling	33
17.9.2	Procedure.....	33
17.9.3	Test voltages	33
17.9.4	Requirements	34
17.10	Hot set test for EPR, HEPR and XLPE insulations and elastomeric sheaths.....	34
17.10.1	Procedure.....	34
17.10.2	Requirements	34
17.11	Bending test on interlock armour cable followed by examination	34
18	Type tests, electrical	34
18.1	General.....	34
18.2	Cables having conductor screens and insulation screens.....	34
18.2.1	General	34
18.2.2	Sequence of tests.....	35
18.2.3	Special provisions	35
18.2.4	Bending test	35
18.2.5	Partial discharge test.....	36
18.2.6	Tan δ measurement for cables of rated voltage 6/10 (12) kV and above.....	36
18.2.7	Heating cycle test.....	36
18.2.8	Impulse test followed by a voltage test	37
18.2.9	Voltage test for 4 h	37
18.2.10	Resistivity of semi-conducting screens	37
18.3	Cables of rated voltage 3,6/6 (7,2) kV having unscreened insulation	38
18.3.1	General	38
18.3.2	Insulation resistance measurement at ambient temperature.....	38
18.3.3	Insulation resistance measurement at maximum conductor temperature	39
18.3.4	Voltage test for 4 h	39
18.3.5	Impulse test.....	39
19	Type tests, non-electrical.....	40
19.1	General.....	40
19.2	Measurement of thickness of insulation.....	40
19.2.1	Sampling	40
19.2.2	Procedure.....	40
19.2.3	Requirements	40
19.3	Measurement of thickness of non-metal sheaths (including extruded separation sheaths, but excluding inner coverings)	40
19.3.1	Sampling	40
19.3.2	Procedure.....	40
19.3.3	Requirements	40
19.4	Measurement of thickness of lead sheath	40
19.4.1	Sampling	40
19.4.2	Procedure.....	40
19.4.3	Requirements	40
19.5	Tests for determining the mechanical properties of insulation before and after ageing	40

19.5.1	Sampling	40
19.5.2	Ageing treatments	41
19.5.3	Conditioning and mechanical tests.....	41
19.5.4	Requirements	41
19.6	Tests for determining the mechanical properties of non-metal sheaths before and after ageing.....	41
19.6.1	Sampling	41
19.6.2	Ageing treatments	41
19.6.3	Conditioning and mechanical tests.....	41
19.6.4	Requirements	41
19.7	Additional ageing test on pieces of completed cables.....	41
19.7.1	General	41
19.7.2	Sampling	41
19.7.3	Ageing treatment	41
19.7.4	Mechanical tests.....	42
19.7.5	Requirements	42
19.8	Loss of mass test on PVC sheaths of type ST ₂	42
19.8.1	Procedure.....	42
19.8.2	Requirements	42
19.9	Pressure test at high temperature on insulations and non-metal sheaths	42
19.9.1	Procedure.....	42
19.9.2	Requirements	42
19.10	Test on PVC insulation, and PVC sheaths and halogen free sheaths at low temperatures	42
19.10.1	Procedure.....	42
19.10.2	Requirements	42
19.11	Test for resistance of PVC insulation and sheaths to cracking (heat shock test).....	42
19.11.1	Procedure.....	42
19.11.2	Requirements	42
19.12	Ozone resistance test for EPR and HEPR insulations	43
19.12.1	Procedure.....	43
19.12.2	Requirements	43
19.13	Hot set test for EPR, HEPR and XLPE insulations and elastomeric sheaths.....	43
19.14	Oil immersion test for elastomeric sheaths.....	43
19.14.1	Procedure.....	43
19.14.2	Requirements	43
19.15	Water absorption test on insulation	43
19.15.1	Procedure.....	43
19.15.2	Requirements	43
19.16	Flame spread test on single cables	43
19.16	Test under fire conditions.....	43
19.16.1	General	43
19.16.2	Flame spread test for single cables	43
19.16.3	Flame spread test for bunched cables	44
19.16.4	Measurement of smoke density of cables burning under defined conditions	44

19.16.5	Determination of acidity (by pH measurement) and conductivity of gases evolved during combustion of the non-metallic materials in the cable.....	44
19.16.6	Fire performance tests on halogen free oversheath material ST ₈	44
19.16.7	Fire performance tests on halogen free oversheath material ST ₁₂	45
19.16.8	Measurement of halogen content of gases evolved during combustion of the non-metallic materials in the cable	45
19.17	Measurement of carbon black content of black PE oversheaths	45
19.17.1	Procedure.....	45
19.17.2	Requirements	45
19.18	Shrinkage test for XLPE insulation	46
19.18.1	Procedure.....	46
19.18.2	Requirements	46
19.19	Thermal stability test for PVC insulation.....	46
19.19.1	Procedure.....	46
19.19.2	Requirements	46
19.20	Determination of hardness of HEPR insulation	46
19.20.1	Procedure.....	46
19.20.2	Requirements	46
19.21	Determination of the elastic modulus of HEPR insulation	46
19.21.1	Procedure.....	46
19.21.2	Requirements	46
19.22	Shrinkage test for PE and halogen free oversheaths	46
19.22.1	Procedure.....	46
19.22.2	Requirements	46
19.23	Strippability test for insulation screen.....	47
19.23.1	General	47
19.23.2	Procedure.....	47
19.23.3	Requirements	47
19.24	Water penetration test.....	47
19.25	Additional tests on halogen free oversheath of type ST ₈	48
19.25.1	General	48
19.25.2	Water absorption test for halogen free oversheath of type ST ₈	48
19.25.3	Abrasion test on halogen free oversheath of type ST ₈	48
19.26	Bending test on interlock armour.....	48
20	Electrical tests after installation	48
20.1	General.....	48
20.2	DC voltage test of the oversheath	48
20.3	Insulation test AC voltage test of the insulation	48
Annex A (normative) Fictitious calculation method for determination of dimensions of protective coverings.....		58
A.1	General.....	58
A.2	Method	58
A.2.1	Conductors	58
A.2.2	Cores	59
A.2.3	Diameter over laid-up cores.....	59
A.2.4	Inner coverings.....	59
A.2.5	Concentric conductors and metal screens.....	60

A.2.6	Lead sheath.....	61
A.2.7	Separation sheath	61
A.2.8	Lapped bedding.....	61
A.2.9	Additional bedding for tape-armoured cables (provided over the inner covering).....	62
A.2.10	Armour	62
Annex B (informative) Tabulated continuous current ratings for cables having extruded insulation and a rated voltage from 3,6/6 kV up to 18/30 kV		63
B.1	General.....	63
B.2	Cable constructions	63
B.3	Temperatures	63
B.4	Soil thermal resistivity	64
B.5	Methods of installation	64
B.5.1	General	64
B.5.2	Single-core cables in air	64
B.5.3	Single-core cables buried direct.....	64
B.5.4	Single-core cables in earthenware ducts.....	65
B.5.5	Three-core cables.....	65
B.6	Screen bonding.....	66
B.7	Cable loading.....	66
B.8	Rating factors for grouped circuits	66
B.9	Correction factors	66
Annex C (normative) Rounding of numbers.....		82
C.1	Rounding of numbers for the purpose of the fictitious calculation method.....	82
C.2	Rounding of numbers for other purposes	82
Annex D (normative) Method of measuring resistivity of semi-conducting screens		83
Annex E (normative) Determination of hardness of HEPR insulations		86
E.1	Test piece.....	86
E.2	Test procedure.....	86
E.2.1	General	86
E.2.2	Surfaces of large radius of curvature	86
E.2.3	Surfaces of small radius of curvature	86
E.2.4	Conditioning and test temperature	86
E.2.5	Number of measurements.....	87
Annex F (normative) Water penetration test.....		88
F.1	Test piece	88
F.2	Test	88
F.3	Requirements	89
Annex G (informative) Determination of the cable conductor temperature		90
G.1	Purpose	90
G.2	Calibration of the temperature of the main test loop	90
G.2.1	General	90
G.2.2	Installation of cable and temperature sensors	90
G.2.3	Calibration method	92
G.3	Heating for the test	93
G.3.1	Method 1 – Test using a reference cable	93
G.3.2	Method 2 – Test using conductor temperature calculations and measurement of the surface temperature	93

Annex H (normative) Test for water penetration in the conductor	95
H.1 General.....	95
H.2 Test piece	95
H.3 Test	95
H.4 Requirements	95
Annex I (normative) Methods of determining the weighted value of halogen content of the non-metallic materials in the cable	97
I.1 Calculating the weighted value of the cable when the halogen content of individual materials is tested	97
I.2 Preparation of the test sample for measurement of halogen content on a sample representative of the non-metallic materials in the cable	97
Bibliography.....	98
Figure B.1 – Single-core cables in air	64
Figure B.2 – Single-core cables buried direct.....	65
Figure B.3 – Single-core cables in earthenware ducts.....	65
Figure B.4 – Three-core cables.....	66
Figure D.1 – Preparation of samples for measurement of resistivity of conductor and insulation screens.....	85
Figure E.1 – Test on surfaces of large radius of curvature	87
Figure E.2 – Test on surfaces of small radius of curvature	87
Figure F.1 – Schematic diagram of apparatus for water penetration test	89
Figure G.1 – Typical test set-up for the reference loop and the main test loop	91
Figure G.2 – Example of an arrangement of the temperature sensors on the conductor of the reference loop.....	92
Figure H.1 – Schematic diagram of apparatus for water penetration test in the conductor.....	96
Table 1 – Recommended rated voltages U_0	17
Table 2 – Insulating compounds.....	17
Table 3 – Maximum conductor temperatures for different types of insulating compound.....	18
Table 4 – Maximum conductor temperatures for different types of sheathing compound	18
Table 5 – Nominal thickness of PVC/B insulation	19
Table 6 – Nominal thickness of cross-linked polyethylene (XLPE) insulation	19
Table 7 – Nominal thickness of ethylene propylene rubber (EPR) and hard ethylene propylene rubber (HEPR) insulation.....	20
Table 8 – Thickness of extruded inner covering	21
Table 9 – Nominal diameter of round armour wires	26
Table 10 – Nominal thickness of armour tapes.....	26
Table 24 – Nominal thickness of armour strips.....	26
Table 11 – Routine test voltages.....	30
Table 12 – Number of samples for sample tests.....	31
Table 13 – Sample test voltages	34
Table 14 – Impulse voltages	37
Table 15 – Electrical type test requirements for insulating compounds.....	49
Table 16 – Non-electrical type tests (see Table 17 to Table 23 and Table 25).....	50

Table 17 – Test requirements for mechanical characteristics of insulating compounds (before and after ageing)	51
Table 18 – Test requirements for particular characteristics for PVC insulating compound	52
Table 19 – Test requirements for particular characteristics of various crosslinked insulating compounds	53
Table 20 – Test requirements for mechanical characteristics of sheathing compounds (before and after ageing)	54
Table 21 – Test requirements for particular characteristics for PVC sheathing compounds	54
Table 22 – Test requirements for particular characteristics of PE (thermoplastic polyethylene) sheathing compounds	55
Table 23 – Test requirements for particular characteristics of elastomeric sheathing compound	55
Table 25 – Test requirements for particular characteristics of halogen free sheathing compounds	56
Table A.1 – Fictitious diameter of conductor	59
Table A.2 – Increase of diameter for concentric conductors and metal screens	60
Table A.3 – Increase of diameter for additional bedding	62
Table A.4 – Increase of diameter over interlocked armour	62
Table B.1 – Nominal screen cross-sectional areas	63
Table B.2 – Current ratings for single-core cables with XLPE insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor	67
Table B.3 – Current ratings for single-core cables with XLPE insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor	68
Table B.4 – Current ratings for single-core cables with EPR insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor	69
Table B.5 – Current ratings for single-core cables with EPR insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor	70
Table B.6 – Current rating for three-core XLPE insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor, armoured and unarmoured	71
Table B.7 – Current rating for three-core XLPE insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor, armoured and unarmoured	72
Table B.8 – Current rating for three-core EPR insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor, armoured and unarmoured	73
Table B.9 – Current rating for three-core EPR insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor, armoured and unarmoured	74
Table B.10 – Correction factors for ambient air temperatures other than 30 °C	74
Table B.11 – Correction factors for ambient ground temperatures other than 20 °C	75
Table B.12 – Correction factors for depths of laying other than 0,8 m for direct buried cables	75
Table B.13 – Correction factors for depths of laying other than 0,8 m for cables in ducts	75
Table B.14 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for direct buried single-core cables	76
Table B.15 – Correction factors for soil thermal resistivities other than 1,5 K·m/W single-core cables in buried ducts	76
Table B.16 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for direct buried three-core cables	77

Table B.17 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for three-core cables in ducts 77

Table B.18 – Correction factors for groups of three-core cables in horizontal formation laid direct in the ground 78

Table B.19 – Correction factors for groups of three-phase circuits of single-core cables laid direct in the ground 78

Table B.20 – Correction factors for groups of three-core cables in single way ducts in horizontal formation 79

Table B.21 – Correction factors for groups of three-phase circuits of single-core cables in single-way ducts 79

Table B.22 – Reduction factors for groups of more than one multi-core cable in air – To be applied to the current-carrying capacity for one multi-core cable in free air 80

Table B.23 – Reduction factors for groups of more than one circuit of single-core cables (Note 2) – To be applied to the current-carrying capacity for one circuit of single-core cables in free air 81

INTERNATIONAL ELECTROTECHNICAL COMMISSION

POWER CABLES WITH EXTRUDED INSULATION AND THEIR ACCESSORIES FOR RATED VOLTAGES FROM 1 kV ($U_m = 1,2$ kV) UP TO 30 kV ($U_m = 36$ kV) –

Part 2: Cables for rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60502-2 edition 3.1 contains the third edition (2014-02) [documents 20/1469A/FDIS and 20/1472/RVD] and its amendment 1 (2024-05) [documents 20/2166/FDIS and 20/2181/RVD].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough

red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 60502-2 has been prepared by IEC technical committee 20: Electric cables.

This third edition cancels and replaces the second edition, published in 2005, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) a simplified calculation procedure for the thickness of the lead sheath and the oversheath;
- b) a new subclause for the determination of the cable conductor temperature;
- c) a modified procedure for the routine voltage test;
- d) a new subclause for a routine electrical test on oversheath;
- e) modified requirements for the non-metal sheaths including semi-conductive layer;
- f) modified tolerances for the bending test cylinder;
- g) the inclusion of a 0,1Hz test after installation.

In addition, the modified structure of the IEC 60811 series has been adopted for this third edition.

The following editorial changes have been made within the English version:

- 'metallic' has been replaced by 'metal';
- 'thermosetting' has been replaced by 'crosslinked'.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60502 series, published under the general title *Power cables with extruded insulation and their accessories for rated voltages from 1kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV)*, can be found on the IEC website.

The committee has decided that the contents of this document and its amendment will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

POWER CABLES WITH EXTRUDED INSULATION AND THEIR ACCESSORIES FOR RATED VOLTAGES FROM 1 kV ($U_m = 1,2$ kV) UP TO 30 kV ($U_m = 36$ kV) –

Part 2: Cables for rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)

1 Scope

This part of IEC 60502 specifies the construction, dimensions and test requirements of power cables with extruded solid insulation from 6 kV up to 30 kV for fixed installations such as distribution networks or industrial installations.

When determining applications, it is recommended that the possible risk of radial water ingress is considered. Cable designs with barriers claimed to prevent longitudinal water penetration and an associated test are included in this part of IEC 60502.

Cables for special installation and service conditions are not included, for example cables for overhead networks, the mining industry, nuclear power plants (in and around the containment area) nor for submarine use or shipboard application.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60038, *IEC standard voltages*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements*

IEC 60060-3, *High-voltage test techniques – Part 3: Definitions and requirements for on-site testing*

IEC 60183, *Guide to the selection of high-voltage cables*

IEC 60228, *Conductors of insulated cables*

IEC 60229:2007, *Tests on cable oversheaths which have a special protective function and are applied by extrusion*

IEC 60230, *Impulse tests on cables and their accessories*

IEC 60287-3-1, *Electric cables – Calculation of the current rating – Part 3: Sections on operating conditions – Section 1: Reference operating conditions and selection of cable type*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-24, *Tests on electric and optical fibre cables under fire conditions – Part 3-24: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category C*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60754-3, *Test on gases evolved during combustion of materials from cables – Part 3: Measurement of low level of halogen content by ion chromatography*

IEC 60811 (all parts), *Electric and optical fibre cables – Test methods for non-metallic materials*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-402, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 402: Miscellaneous tests – Water absorption tests*

IEC 60811-403, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 403: Miscellaneous tests – Ozone resistance test on cross-linked compounds*

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths*

IEC 60811-405, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 405: Miscellaneous tests – Thermal stability test for PVC insulations and PVC sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-502, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 502: Mechanical tests – Shrinkage test for insulations*

IEC 60811-503, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 503: Mechanical tests – Shrinkage test for sheaths*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 506: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-507, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 507: Mechanical tests – Hot set test for cross-linked materials*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 60811-605, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 605: Physical tests – Measurement of carbon black and/or mineral filler in polyethylene compounds*

IEC 60811-606, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 606: Physical tests – Methods for determining the density*

IEC 60853 (all parts), *Calculation of the cyclic and emergency current rating of cables*

IEC 60853-2, *Calculation of the cyclic and emergency current rating of cables – Part 2: Cyclic rating of cables greater than 18/30 (36) kV and emergency ratings for cables of all voltages*

IEC 60885-3, *Electrical test methods for electric cables – Part 3: Test methods for partial discharge measurements on lengths of extruded power cables*

IEC 60986, *Short-circuit temperature limits of electric cables with rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

ISO 48, *Rubber, vulcanized or thermoplastic – Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

CONTENTS

FOREWORD.....	11
1 Scope.....	13
2 Normative references	13
3 Terms and definitions	15
3.1 Definitions of dimensional values (thicknesses, cross-sections, etc.)	15
3.2 Definitions concerning the tests	16
4 Voltage designations and materials	16
4.1 Rated voltages.....	16
4.2 Insulating compounds	17
4.3 Sheathing compounds.....	18
5 Conductors.....	19
6 Insulation.....	19
6.1 Material	19
6.2 Insulation thickness	19
7 Screening.....	20
7.1 General.....	20
7.2 Conductor screen.....	20
7.3 Insulation screen	20
8 Assembly of three-core cables, inner coverings and fillers	21
8.1 General.....	21
8.2 Inner coverings and fillers	21
8.2.1 Construction	21
8.2.2 Material	21
8.2.3 Thickness of extruded inner covering.....	21
8.2.4 Thickness of lapped inner covering.....	21
8.3 Cables having a collective metal layer (see Clause 9).....	22
8.4 Cables having a metal layer over each individual core (see Clause 10).....	22
9 Metal layers for single-core and three-core cables.....	22
10 Metal screen.....	22
10.1 Construction	22
10.2 Requirements	23
10.3 Metal screens not associated with semi-conducting layers	23
11 Concentric conductor.....	23
11.1 Construction	23
11.2 Requirements	23
11.3 Application.....	23
12 Metal sheath.....	23
12.1 Lead sheath.....	23
12.2 Other metal sheaths.....	23
13 Metal armour	24
13.1 Types of metal armour	24
13.2 Materials.....	24
13.3 Application of armour	24
13.3.1 Single-core cables.....	24
13.3.2 Three-core cables.....	24

13.3.3	Separation sheath	24
13.3.4	Lapped bedding under armour for lead sheathed cables	25
13.4	Dimensions of the armour wires, armour tapes and armour strips	25
13.5	Correlation between cable diameters and armour dimensions	25
13.6	Round or flat wire armour.....	26
13.7	Double tape armour	26
13.8	Interlock metal tape armour	27
14	Oversheath.....	27
14.1	General.....	27
14.2	Material	27
14.3	Thickness	28
15	Test conditions	28
15.1	Ambient temperature.....	28
15.2	Frequency and waveform of power frequency test voltages.....	28
15.3	Waveform of impulse test voltages.....	28
15.4	Determination of the cable conductor temperature	28
16	Routine tests	28
16.1	General.....	28
16.2	Electrical resistance of conductors	29
16.3	Partial discharge test	29
16.4	Voltage test	29
16.4.1	General	29
16.4.2	Test procedure for single-core cables	29
16.4.3	Test procedure for three-core cables	29
16.4.4	Test voltage.....	30
16.4.5	Requirement.....	30
16.5	Electrical test on oversheath of the cable.....	30
17	Sample tests	30
17.1	General.....	30
17.2	Frequency of sample tests	30
17.2.1	Conductor examination and check of dimensions.....	30
17.2.2	Electrical and physical tests.....	30
17.3	Repetition of tests.....	31
17.4	Conductor examination	31
17.5	Measurement of thickness of insulation and of non-metal sheaths (including extruded separation sheaths, but excluding inner extruded coverings).....	31
17.5.1	General	31
17.5.2	Requirements for the insulation	31
17.5.3	Requirements for the non-metal sheaths.....	32
17.6	Measurement of thickness of lead sheath	32
17.6.1	General	32
17.6.2	Strip method	32
17.6.3	Ring method	32
17.7	Measurement of armour wires, tapes and armour strips	32
17.7.1	Measurement on wires.....	32
17.7.2	Measurement on tapes and armour strips	33
17.7.3	Requirements	33

17.8	Measurement of external diameter	33
17.9	Voltage test for 4 h	33
17.9.1	Sampling	33
17.9.2	Procedure.....	33
17.9.3	Test voltages	33
17.9.4	Requirements	33
17.10	Hot set test for EPR, HEPR and XLPE insulations and elastomeric sheaths.....	34
17.10.1	Procedure.....	34
17.10.2	Requirements	34
17.11	Bending test on interlock armour cable followed by examination	34
18	Type tests, electrical	34
18.1	General.....	34
18.2	Cables having conductor screens and insulation screens.....	34
18.2.1	General	34
18.2.2	Sequence of tests.....	34
18.2.3	Special provisions	35
18.2.4	Bending test	35
18.2.5	Partial discharge test.....	36
18.2.6	Tan δ measurement for cables of rated voltage 6/10 (12) kV and above.....	36
18.2.7	Heating cycle test.....	36
18.2.8	Impulse test followed by a voltage test	36
18.2.9	Voltage test for 4 h	37
18.2.10	Resistivity of semi-conducting screens	37
18.3	Cables of rated voltage 3,6/6 (7,2) kV having unscreened insulation	37
18.3.1	General	37
18.3.2	Insulation resistance measurement at ambient temperature.....	38
18.3.3	Insulation resistance measurement at maximum conductor temperature	38
18.3.4	Voltage test for 4 h	39
18.3.5	Impulse test.....	39
19	Type tests, non-electrical.....	39
19.1	General.....	39
19.2	Measurement of thickness of insulation.....	39
19.2.1	Sampling	39
19.2.2	Procedure.....	39
19.2.3	Requirements	40
19.3	Measurement of thickness of non-metal sheaths (including extruded separation sheaths, but excluding inner coverings)	40
19.3.1	Sampling	40
19.3.2	Procedure.....	40
19.3.3	Requirements	40
19.4	Measurement of thickness of lead sheath	40
19.4.1	Sampling	40
19.4.2	Procedure.....	40
19.4.3	Requirements	40
19.5	Tests for determining the mechanical properties of insulation before and after ageing	40

	19.5.1 Sampling	40
	19.5.2 Ageing treatments	40
	19.5.3 Conditioning and mechanical tests.....	40
	19.5.4 Requirements	40
19.6	Tests for determining the mechanical properties of non-metal sheaths before and after ageing.....	41
	19.6.1 Sampling	41
	19.6.2 Ageing treatments	41
	19.6.3 Conditioning and mechanical tests.....	41
	19.6.4 Requirements	41
19.7	Additional ageing test on pieces of completed cables.....	41
	19.7.1 General	41
	19.7.2 Sampling	41
	19.7.3 Ageing treatment	41
	19.7.4 Mechanical tests.....	41
	19.7.5 Requirements	41
19.8	Loss of mass test on PVC sheaths of type ST ₂	42
	19.8.1 Procedure.....	42
	19.8.2 Requirements	42
19.9	Pressure test at high temperature on insulations and non-metal sheaths	42
	19.9.1 Procedure.....	42
	19.9.2 Requirements	42
19.10	Test on PVC insulation, PVC sheaths and halogen free sheaths at low temperatures	42
	19.10.1 Procedure.....	42
	19.10.2 Requirements	42
19.11	Test for resistance of PVC insulation and sheaths to cracking (heat shock test).....	42
	19.11.1 Procedure.....	42
	19.11.2 Requirements	42
19.12	Ozone resistance test for EPR and HEPR insulations	42
	19.12.1 Procedure.....	42
	19.12.2 Requirements	42
19.13	Hot set test for EPR, HEPR and XLPE insulations and elastomeric sheaths.....	43
19.14	Oil immersion test for elastomeric sheaths.....	43
	19.14.1 Procedure.....	43
	19.14.2 Requirements	43
19.15	Water absorption test on insulation	43
	19.15.1 Procedure.....	43
	19.15.2 Requirements	43
19.16	Test under fire conditions.....	43
	19.16.1 General	43
	19.16.2 Flame spread test for single cables	43
	19.16.3 Flame spread test for bunched cables	43
	19.16.4 Measurement of smoke density of cables burning under defined conditions	43
	19.16.5 Determination of acidity (by pH measurement) and conductivity of gases evolved during combustion of the non-metallic materials in the cable.....	44

	19.16.6 Fire performance tests on halogen free oversheath material ST ₈	44
	19.16.7 Fire performance tests on halogen free oversheath material ST ₁₂	44
	19.16.8 Measurement of halogen content of gases evolved during combustion of the non-metallic materials in the cable	45
19.17	Measurement of carbon black content of black PE oversheaths	45
	19.17.1 Procedure.....	45
	19.17.2 Requirements	45
19.18	Shrinkage test for XLPE insulation	45
	19.18.1 Procedure.....	45
	19.18.2 Requirements	45
19.19	Thermal stability test for PVC insulation.....	46
	19.19.1 Procedure.....	46
	19.19.2 Requirements	46
19.20	Determination of hardness of HEPR insulation	46
	19.20.1 Procedure.....	46
	19.20.2 Requirements	46
19.21	Determination of the elastic modulus of HEPR insulation	46
	19.21.1 Procedure.....	46
	19.21.2 Requirements	46
19.22	Shrinkage test for PE and halogen free oversheaths	46
	19.22.1 Procedure.....	46
	19.22.2 Requirements	46
19.23	Strippability test for insulation screen.....	46
	19.23.1 General	46
	19.23.2 Procedure.....	47
	19.23.3 Requirements	47
19.24	Water penetration test.....	47
19.25	Additional tests on halogen free oversheath of type ST ₈	47
	19.25.1 General	47
	19.25.2 Water absorption test for halogen free oversheath of type ST ₈	48
	19.25.3 Abrasion test on halogen free oversheath of type ST ₈	48
19.26	Bending test on interlock armour.....	48
20	Electrical tests after installation	48
	20.1 General.....	48
	20.2 DC voltage test of the oversheath	48
	20.3 AC voltage test of the insulation.....	48
Annex A (normative) Fictitious calculation method for determination of dimensions of protective coverings.....		57
	A.1 General.....	57
	A.2 Method	57
	A.2.1 Conductors	57
	A.2.2 Cores	58
	A.2.3 Diameter over laid-up cores.....	58
	A.2.4 Inner coverings.....	58
	A.2.5 Concentric conductors and metal screens.....	59
	A.2.6 Lead sheath.....	60
	A.2.7 Separation sheath	60

A.2.8	Lapped bedding	60
A.2.9	Additional bedding for tape-armoured cables (provided over the inner covering).....	61
A.2.10	Armour	61
Annex B (informative)	Tabulated continuous current ratings for cables having extruded insulation and a rated voltage from 3,6/6 kV up to 18/30 kV	62
B.1	General.....	62
B.2	Cable constructions	62
B.3	Temperatures	62
B.4	Soil thermal resistivity	63
B.5	Methods of installation	63
B.5.1	General	63
B.5.2	Single-core cables in air	63
B.5.3	Single-core cables buried direct.....	63
B.5.4	Single-core cables in earthenware ducts.....	64
B.5.5	Three-core cables.....	64
B.6	Screen bonding.....	65
B.7	Cable loading.....	65
B.8	Rating factors for grouped circuits	65
B.9	Correction factors	65
Annex C (normative)	Rounding of numbers	81
C.1	Rounding of numbers for the purpose of the fictitious calculation method.....	81
C.2	Rounding of numbers for other purposes	81
Annex D (normative)	Method of measuring resistivity of semi-conducting screens	82
Annex E (normative)	Determination of hardness of HEPR insulations	85
E.1	Test piece	85
E.2	Test procedure.....	85
E.2.1	General	85
E.2.2	Surfaces of large radius of curvature	85
E.2.3	Surfaces of small radius of curvature	85
E.2.4	Conditioning and test temperature	85
E.2.5	Number of measurements.....	86
Annex F (normative)	Water penetration test.....	87
F.1	Test piece	87
F.2	Test	87
F.3	Requirements	88
Annex G (informative)	Determination of the cable conductor temperature	89
G.1	Purpose	89
G.2	Calibration of the temperature of the main test loop	89
G.2.1	General	89
G.2.2	Installation of cable and temperature sensors	89
G.2.3	Calibration method	91
G.3	Heating for the test	92
G.3.1	Method 1 – Test using a reference cable	92
G.3.2	Method 2 – Test using conductor temperature calculations and measurement of the surface temperature	92
Annex H (normative)	Test for water penetration in the conductor	94
H.1	General.....	94

H.2	Test piece	94
H.3	Test	94
H.4	Requirements	94
Annex I (normative) Methods of determining the weighted value of halogen content of the non-metallic materials in the cable		96
I.1	Calculating the weighted value of the cable when the halogen content of individual materials is tested	96
I.2	Preparation of the test sample for measurement of halogen content on a sample representative of the non-metallic materials in the cable	96
Bibliography		97
Figure B.1 – Single-core cables in air		63
Figure B.2 – Single-core cables buried direct		64
Figure B.3 – Single-core cables in earthenware ducts		64
Figure B.4 – Three-core cables		65
Figure D.1 – Preparation of samples for measurement of resistivity of conductor and insulation screens		84
Figure E.1 – Test on surfaces of large radius of curvature		86
Figure E.2 – Test on surfaces of small radius of curvature		86
Figure F.1 – Schematic diagram of apparatus for water penetration test		88
Figure G.1 – Typical test set-up for the reference loop and the main test loop		90
Figure G.2 – Example of an arrangement of the temperature sensors on the conductor of the reference loop		91
Figure H.1 – Schematic diagram of apparatus for water penetration test in the conductor		95
Table 1 – Recommended rated voltages U_0		17
Table 2 – Insulating compounds		17
Table 3 – Maximum conductor temperatures for different types of insulating compound		18
Table 4 – Maximum conductor temperatures for different types of sheathing compound		18
Table 5 – Nominal thickness of PVC/B insulation		19
Table 6 – Nominal thickness of cross-linked polyethylene (XLPE) insulation		19
Table 7 – Nominal thickness of ethylene propylene rubber (EPR) and hard ethylene propylene rubber (HEPR) insulation		20
Table 8 – Thickness of extruded inner covering		21
Table 9 – Nominal diameter of round armour wires		26
Table 10 – Nominal thickness of armour tapes		26
Table 24 – Nominal thickness of armour strips		26
Table 11 – Routine test voltages		30
Table 12 – Number of samples for sample tests		31
Table 13 – Sample test voltages		33
Table 14 – Impulse voltages		37
Table 15 – Electrical type test requirements for insulating compounds		49
Table 16 – Non-electrical type tests (see Table 17 to Table 23 and Table 25)		49
Table 17 – Test requirements for mechanical characteristics of insulating compounds (before and after ageing)		50

Table 18 – Test requirements for particular characteristics for PVC insulating compound.....	51
Table 19 – Test requirements for particular characteristics of various crosslinked insulating compounds	52
Table 20 – Test requirements for mechanical characteristics of sheathing compounds (before and after ageing)	53
Table 21 – Test requirements for particular characteristics for PVC sheathing compounds	53
Table 22 – Test requirements for particular characteristics of PE (thermoplastic polyethylene) sheathing compounds	54
Table 23 – Test requirements for particular characteristics of elastomeric sheathing compound.....	54
Table 25 – Test requirements for particular characteristics of halogen free sheathing compounds	55
Table A.1 – Fictitious diameter of conductor	58
Table A.2 – Increase of diameter for concentric conductors and metal screens.....	59
Table A.3 – Increase of diameter for additional bedding.....	61
Table A.4 – Increase of diameter over interlocked armour.....	61
Table B.1 – Nominal screen cross-sectional areas	62
Table B.2 – Current ratings for single-core cables with XLPE insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor	66
Table B.3 – Current ratings for single-core cables with XLPE insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor.....	67
Table B.4 – Current ratings for single-core cables with EPR insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor	68
Table B.5 – Current ratings for single-core cables with EPR insulation – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor.....	69
Table B.6 – Current rating for three-core XLPE insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor, armoured and unarmoured	70
Table B.7 – Current rating for three-core XLPE insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor, armoured and unarmoured.....	71
Table B.8 – Current rating for three-core EPR insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Copper conductor, armoured and unarmoured	72
Table B.9 – Current rating for three-core EPR insulated cables – Rated voltage 3,6/6 kV to 18/30 kV * – Aluminium conductor, armoured and unarmoured.....	73
Table B.10 – Correction factors for ambient air temperatures other than 30 °C	73
Table B.11 – Correction factors for ambient ground temperatures other than 20 °C	74
Table B.12 – Correction factors for depths of laying other than 0,8 m for direct buried cables.....	74
Table B.13 – Correction factors for depths of laying other than 0,8 m for cables in ducts	74
Table B.14 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for direct buried single-core cables	75
Table B.15 – Correction factors for soil thermal resistivities other than 1,5 K·m/W single-core cables in buried ducts	75
Table B.16 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for direct buried three-core cables.....	76
Table B.17 – Correction factors for soil thermal resistivities other than 1,5 K·m/W for three-core cables in ducts.....	76

Table B.18 – Correction factors for groups of three-core cables in horizontal formation laid direct in the ground 77

Table B.19 – Correction factors for groups of three-phase circuits of single-core cables laid direct in the ground 77

Table B.20 – Correction factors for groups of three-core cables in single way ducts in horizontal formation 78

Table B.21 – Correction factors for groups of three-phase circuits of single-core cables in single-way ducts 78

Table B.22 – Reduction factors for groups of more than one multi-core cable in air – To be applied to the current-carrying capacity for one multi-core cable in free air 79

Table B.23 – Reduction factors for groups of more than one circuit of single-core cables (Note 2) – To be applied to the current-carrying capacity for one circuit of single-core cables in free air 80

INTERNATIONAL ELECTROTECHNICAL COMMISSION

POWER CABLES WITH EXTRUDED INSULATION AND THEIR ACCESSORIES FOR RATED VOLTAGES FROM 1 kV ($U_m = 1,2$ kV) UP TO 30 kV ($U_m = 36$ kV) –

Part 2: Cables for rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60502-2 edition 3.1 contains the third edition (2014-02) [documents 20/1469A/FDIS and 20/1472/RVD] and its amendment 1 (2024-05) [documents 20/2166/FDIS and 20/2181/RVD].

This Final version does not show where the technical content is modified by amendment 1. A separate Redline version with all changes highlighted is available in this publication.

International Standard IEC 60502-2 has been prepared by IEC technical committee 20: Electric cables.

This third edition cancels and replaces the second edition, published in 2005, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) a simplified calculation procedure for the thickness of the lead sheath and the oversheath;
- b) a new subclause for the determination of the cable conductor temperature;
- c) a modified procedure for the routine voltage test;
- d) a new subclause for a routine electrical test on oversheath;
- e) modified requirements for the non-metal sheaths including semi-conductive layer;
- f) modified tolerances for the bending test cylinder;
- g) the inclusion of a 0,1Hz test after installation.

In addition, the modified structure of the IEC 60811 series has been adopted for this third edition.

The following editorial changes have been made within the English version:

- 'metallic' has been replaced by 'metal';
- 'thermosetting' has been replaced by 'crosslinked'.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60502 series, published under the general title *Power cables with extruded insulation and their accessories for rated voltages from 1kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV)*, can be found on the IEC website.

The committee has decided that the contents of this document and its amendment will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

**POWER CABLES WITH EXTRUDED INSULATION
AND THEIR ACCESSORIES FOR RATED VOLTAGES
FROM 1 kV ($U_m = 1,2$ kV) UP TO 30 kV ($U_m = 36$ kV) –**

**Part 2: Cables for rated voltages from 6 kV
($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)**

1 Scope

This part of IEC 60502 specifies the construction, dimensions and test requirements of power cables with extruded solid insulation from 6 kV up to 30 kV for fixed installations such as distribution networks or industrial installations.

When determining applications, it is recommended that the possible risk of radial water ingress is considered. Cable designs with barriers claimed to prevent longitudinal water penetration and an associated test are included in this part of IEC 60502.

Cables for special installation and service conditions are not included, for example cables for overhead networks, the mining industry, nuclear power plants (in and around the containment area) nor for submarine use or shipboard application.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60038, *IEC standard voltages*

IEC 60060-1, *High-voltage test techniques – Part 1: General definitions and test requirements*

IEC 60060-3, *High-voltage test techniques – Part 3: Definitions and requirements for on-site testing*

IEC 60183, *Guide to the selection of high-voltage cables*

IEC 60228, *Conductors of insulated cables*

IEC 60229:2007, *Tests on cable oversheaths which have a special protective function and are applied by extrusion*

IEC 60230, *Impulse tests on cables and their accessories*

IEC 60287-3-1, *Electric cables – Calculation of the current rating – Part 3: Sections on operating conditions – Section 1: Reference operating conditions and selection of cable type*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-24, *Tests on electric and optical fibre cables under fire conditions – Part 3-24: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category C*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60754-3, *Test on gases evolved during combustion of materials from cables – Part 3: Measurement of low level of halogen content by ion chromatography*

IEC 60811 (all parts), *Electric and optical fibre cables – Test methods for non-metallic materials*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-402, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 402: Miscellaneous tests – Water absorption tests*

IEC 60811-403, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 403: Miscellaneous tests – Ozone resistance test on cross-linked compounds*

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths*

IEC 60811-405, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 405: Miscellaneous tests – Thermal stability test for PVC insulations and PVC sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-502, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 502: Mechanical tests – Shrinkage test for insulations*

IEC 60811-503, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 503: Mechanical tests – Shrinkage test for sheaths*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 506: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-507, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 507: Mechanical tests – Hot set test for cross-linked materials*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 60811-605, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 605: Physical tests – Measurement of carbon black and/or mineral filler in polyethylene compounds*

IEC 60811-606, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 606: Physical tests – Methods for determining the density*

IEC 60853 (all parts), *Calculation of the cyclic and emergency current rating of cables*

IEC 60853-2, *Calculation of the cyclic and emergency current rating of cables – Part 2: Cyclic rating of cables greater than 18/30 (36) kV and emergency ratings for cables of all voltages*

IEC 60885-3, *Electrical test methods for electric cables – Part 3: Test methods for partial discharge measurements on lengths of extruded power cables*

IEC 60986, *Short-circuit temperature limits of electric cables with rated voltages from 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

ISO 48, *Rubber, vulcanized or thermoplastic – Determination of hardness (hardness between 10 IRHD and 100 IRHD)*