



IEC 60684-3-216

Edition 2.0 2019-08
REDLINE VERSION

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.035.20

ISBN 978-2-8322-7287-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	2
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Bibliography.....	19
Table 1 – Dimensional and mass requirements – Class A	8
Table 2 – Dimensional and mass requirements – Class B	8
Table 3 – Dimensional and mass requirements – Class C	9
Table 4 – Dimensional and mass requirements – Class D	9
Table 5 – Property requirements	9
Table 6 – Requirements for breakdown voltage	16
Table 7 – Resistance to selected fluids	17
Table 8 – Additional property requirements	18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60684-3-216 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2001, Amendment 1:2005 and Amendment 2:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the temperature at which the sleeving is shrunk in a forced-air circulation oven for (5 ± 1) min has been increased from (150 ± 5) °C to (200 ± 5) °C.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/888/FDIS	15/902/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1);

Part 2: Methods of test (IEC 60684-2);

Part 3: Specifications for individual types of sleeving (IEC 60684-3).

This document comprises one of the sheets of Part 3 as follows:

Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

1 Scope

This ~~sheet~~ part of IEC 60684-3 gives the requirements for four types of heat-shrinkable, flame-retarded, limited-fire-hazard sleeving with a thermal endurance rating of 105 °C as shown below.

Class A:	thin wall	shrink ratio 2:1	internal diameter up to 102,0 mm
Class B:	medium wall	shrink ratio 2:1	internal diameter up to 60,0 mm
Class C:	thick wall	shrink ratio 2:1	internal diameter up to 51,0 mm
Class D:	medium wall	shrink ratio 3:1	internal diameter up to 40,0 mm

These sleeves are normally supplied in the following colours: black, red, green, blue, white, yellow and green/yellow.

Sizes or colours other than those listed in this document ~~may be~~ are available as custom items. These items ~~shall be~~ are considered to comply with this document if they comply with the property requirements listed in Tables 5, 6, 7 and 8, excluding dimensions and mass.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application ~~should~~ will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60684-1: ~~1980~~2003, ~~Specification for~~ Flexible insulating sleeving – Part 1: Definitions and general requirements

IEC 60684-2: ~~1997~~2011, Flexible insulating sleeving – Part 2: Methods of test

IEC 60757:1983, Code for designation of colours

ISO 846: ~~1997~~2019, Plastics – Evaluation of the action of microorganisms

ISO 1817: ~~1999~~2015, Rubber, vulcanized or thermoplastic – Determination of the effect of liquids ~~(available in English only)~~

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving**

**Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines –
Feuille 216: Gaines thermorétractables, ignifugées, au risque de feu limité**



CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Bibliography.....	16
Table 1 – Dimensional and mass requirements – Class A	8
Table 2 – Dimensional and mass requirements – Class B	8
Table 3 – Dimensional and mass requirements – Class C	9
Table 4 – Dimensional and mass requirements – Class D	9
Table 5 – Property requirements	10
Table 6 – Requirements for breakdown voltage	13
Table 7 – Resistance to selected fluids	14
Table 8 – Additional property requirements	15

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-216 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2001, Amendment 1:2005 and Amendment 2:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the temperature at which the sleeving is shrunk in a forced-air circulation oven for (5 ± 1) min has been increased from (150 ± 5) °C to (200 ± 5) °C.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/888/FDIS	15/902/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1);

Part 2: Methods of test (IEC 60684-2);

Part 3: Specifications for individual types of sleeving (IEC 60684-3).

This document comprises one of the sheets of Part 3 as follows:

Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 216: Heat-shrinkable, flame-retarded, limited-fire-hazard sleeving

1 Scope

This part of IEC 60684-3 gives the requirements for four types of heat-shrinkable, flame-retarded, limited-fire-hazard sleeving with a thermal endurance rating of 105 °C as shown below.

Class A:	thin wall	shrink ratio 2:1	internal diameter up to 102,0 mm
Class B:	medium wall	shrink ratio 2:1	internal diameter up to 60,0 mm
Class C:	thick wall	shrink ratio 2:1	internal diameter up to 51,0 mm
Class D:	medium wall	shrink ratio 3:1	internal diameter up to 40,0 mm

These sleeveings are normally supplied in the following colours: black, red, green, blue, white, yellow and green/yellow.

Sizes or colours other than those listed in this document are available as custom items. These items are considered to comply with this document if they comply with the property requirements listed in Tables 5, 6, 7 and 8, excluding dimensions and mass.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:2011, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60757:1983, *Code for designation of colours*

ISO 846:2019, *Plastics – Evaluation of the action of microorganisms*

ISO 1817:2015, *Rubber, vulcanized or thermoplastic – Determination of the effect of liquids*

SOMMAIRE

AVANT-PROPOS	19
INTRODUCTION	21
1 Domaine d'application	22
2 Références normatives	22
3 Termes et définitions	23
4 Désignation	23
5 Conditions d'essai	23
6 Exigences	23
7 Conformité des gaines	23
Bibliographie	32
Tableau 1 – Exigences relatives aux dimensions et à la masse – Classe A	24
Tableau 2 – Exigences relatives aux dimensions et à la masse – Classe B	24
Tableau 3 – Exigences relatives aux dimensions et à la masse – Classe C	25
Tableau 4 – Exigences relatives aux dimensions et à la masse – Classe D	25
Tableau 5 – Exigences relatives aux propriétés	26
Tableau 6 – Exigences relatives à la tension de claquage	29
Tableau 7 – Résistance aux fluides choisis	30
Tableau 8 – Exigences complémentaires relatives aux propriétés	31

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

GAINES ISOLANTES SOUPLES –

Partie 3: Spécifications pour types particuliers de gaines – Feuille 216: Gainses thermorétractables, ignifugées, au risque de feu limité

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (IEC) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de l'IEC). L'IEC a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, l'IEC – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de l'IEC"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Les organisations internationales, gouvernementales et non gouvernementales, en liaison avec l'IEC, participent également aux travaux. L'IEC collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de l'IEC concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux de l'IEC intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de l'IEC se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de l'IEC. Tous les efforts raisonnables sont entrepris afin que l'IEC s'assure de l'exactitude du contenu technique de ses publications; l'IEC ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de l'IEC s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de l'IEC dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de l'IEC et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) L'IEC elle-même ne fournit aucune attestation de conformité. Des organismes de certification indépendants fournissent des services d'évaluation de conformité et, dans certains secteurs, accèdent aux marques de conformité de l'IEC. L'IEC n'est responsable d'aucun des services effectués par les organismes de certification indépendants.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à l'IEC, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de l'IEC, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de l'IEC ou de toute autre Publication de l'IEC, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de l'IEC peuvent faire l'objet de droits de brevet. L'IEC ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de brevets et de ne pas avoir signalé leur existence.

La Norme internationale IEC 60684-3-216 a été établie par le comité d'études 15 de l'IEC: Matériaux isolants électriques solides.

Cette deuxième édition annule et remplace la première édition parue en 2001, l'Amendement 1:2005 et l'Amendement 2:2013. Cette édition constitue une révision technique.

Cette édition inclut la modification technique majeure suivante par rapport à l'édition précédente:

- a) la température à laquelle les gaines sont rétreintes dans une étuve à circulation d'air forcée pendant (5 ± 1) min a été augmentée de $(150 \pm 5) ^\circ\text{C}$ à $(200 \pm 5) ^\circ\text{C}$.

Le texte de cette Norme internationale est issu des documents suivants:

FDIS	Rapport de vote
15/888/FDIS	15/902/RVD

Le rapport de vote indiqué dans le tableau ci-dessus donne toute information sur le vote ayant abouti à l'approbation de cette Norme internationale.

Ce document a été rédigé selon les Directives ISO/IEC, Partie 2.

Une liste de toutes les parties de la série IEC 60684, publiées sous le titre général *Gaines isolantes souples*, peut être consultée sur le site web de l'IEC.

Le comité a décidé que le contenu de ce document ne sera pas modifié avant la date de stabilité indiquée sur le site web de l'IEC sous "<http://webstore.iec.ch>" dans les données relatives au document recherché. A cette date, le document sera

- reconduit,
- supprimé,
- remplacé par une édition révisée, ou
- amendé.

INTRODUCTION

La présente Norme internationale fait partie d'une série traitant des gaines isolantes souples à usages électriques.

Cette série est constituée de trois parties:

Partie 1: Définitions et exigences générales (IEC 60684-1);

Partie 2: Méthodes d'essai (IEC 60684-2);

Partie 3: Spécifications pour types particuliers de gaines (IEC 60684-3).

Le présent document contient l'une des feuilles qui composent la Partie 3, comme suit:

Feuille 216: Gains thermorétractables, ignifugées, au risque de feu limité

GAINES ISOLANTES SOUPLES –

Partie 3: Spécifications pour types particuliers de gaines – Feuille 216: Gainés thermorétractables, ignifugés, au risque de feu limité

1 Domaine d'application

La présente partie de l'IEC 60684-3 donne les exigences relatives à quatre types de gaines thermorétractables, ignifugés, au risque de feu limité, ayant un indice d'endurance thermique de 105 °C, comme cela est indiqué ci-dessous.

Classe A: paroi mince rapport de rétreint 2:1 diamètre intérieur allant jusqu'à 102,0 mm
Classe B: paroi moyenne rapport de rétreint 2:1 diamètre intérieur allant jusqu'à 60,0 mm
Classe C: paroi épaisse rapport de rétreint 2:1 diamètre intérieur allant jusqu'à 51,0 mm
Classe D: paroi moyenne rapport de rétreint 3:1 diamètre intérieur allant jusqu'à 40,0 mm

Ces gaines sont normalement disponibles dans les couleurs suivantes: noir, rouge, vert, bleu, blanc, jaune et vert/jaune.

Des dimensions et des couleurs autres que celles indiquées dans le présent document sont disponibles comme articles spéciaux. Ces articles sont considérés comme conformes au présent document s'ils satisfont aux exigences relatives aux propriétés indiquées dans les Tableaux 5, 6, 7 et 8, à l'exception des dimensions et de la masse.

Les matériaux qui sont conformes à la présente spécification satisfont à des niveaux de performances établis. Cependant, le choix d'un matériau par un utilisateur, pour une application spécifique, est fondé sur les exigences réelles nécessaires pour obtenir des performances adéquates pour l'application concernée, et n'est pas fondé sur cette seule spécification.

2 Références normatives

Les documents suivants sont cités dans le texte de sorte qu'ils constituent, pour tout ou partie de leur contenu, des exigences du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

IEC 60684-1:2003, *Spécification pour gaines isolantes souples – Partie 1: Définitions et exigences générales.*

IEC 60684-2:2011, *Gainés isolantes souples – Partie 2: Méthodes d'essai*

IEC 60757:1983, *Code de désignation de couleurs*

ISO 846:2019, *Plastiques – Évaluation de l'action des micro-organismes*

ISO 1817:2015, *Caoutchouc vulcanisé ou thermoplastique – Détermination de l'action des liquides*