

This is a preview - click here to buy the full publication



IEC 60793-1-44

Edition 3.0 2023-07
COMMENTED VERSION

INTERNATIONAL STANDARD



**Optical fibres –
Part 1-44: Measurement methods and test procedures – Cut-off wavelength**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-7323-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	7
3 Terms and definitions	8
4 Background	8
5 Overview of methods	8
6 Reference test method	9
7 Apparatus	9
7.1 Light source	9
7.2 Modulation	10
7.3 Launch optics	10
7.4 Support and positioning apparatus	10
7.5 Deployment mandrel	10
7.5.1 General	10
7.5.2 Cable cut-off wavelength deployment, method A	10
7.5.3 Cable cut-off wavelength deployment, method B	11
7.5.4 Fibre cut-off wavelength deployment, method C	12
7.6 Detection optics	13
7.7 Detector assembly and signal detection electronics	14
7.8 Cladding mode stripper	14
8 Sampling and specimens	14
8.1 Specimen length	14
8.2 Specimen end face	14
9 Procedure	14
9.1 Positioning of specimen in apparatus	14
9.1.1 General requirements for all methods	14
9.1.2 Deployment requirements for each method	14
9.2 Measurement of output power	14
9.2.1 Overview	14
9.2.2 Bend-reference technique	15
9.2.3 Multimode-reference technique	16
10 Calculations	16
10.1 Bend-reference technique	16
10.2 Multimode-reference technique	16
10.3 Curve fitting technique for improved precision (optional)	14
 10.3.1 General
 10.3.2 Step 1, define the upper wavelength region
 10.3.3 Step 2, characterize the attenuation curve
 10.3.4 Step 3, determine the upper wavelength of the transition region
 10.3.5 Step 4, determine the lower wavelength of the transition region
 10.3.6 Step 5, characterize the transition region with the theoretical model
 10.3.7 Step 6, compute the cut-off wavelength, λ_c
11 Mapping functions	21
12 Results	21
13 Specification information	22

Annex A (normative) Requirements specific to method A – Cable cut-off wavelength, λ_{CC} , using uncabled fibre.....	23
A.1 Specimen length.....	23
A.2 Procedure – Position specimen on deployment mandrel.....	23
Annex B (normative) Requirements specific to method B – Cable cut-off wavelength, λ_{CC} , using cabled fibre	24
B.1 Specimen length.....	24
B.2 Procedure – Position specimen on deployment mandrel.....	24
Annex C (normative) Requirements specific to method C – Fibre cut-off wavelength, λ_C	25
C.1 Specimen length.....	25
C.2 Procedure – Position specimen on deployment mandrel.....	25
Annex D (informative) Cut-off curve artifacts	27
D.1 Description of curve artifacts.....	27
D.2 Curve-fitting technique for artifact filtering	27
D.2.1 Overview.....	27
D.2.2 General.....	28
D.2.3 Step 1: define the upper wavelength region.....	29
D.2.4 Step 2: characterize the spectral transmittance	29
D.2.5 Step 3: calculate the deviation of the spectral transmittance from the linear fit.....	29
D.2.6 Step 4: determine the end wavelength of the transition region.....	30
D.2.7 Step 5: determine the start wavelength of the transition region.....	30
D.2.8 Step 6: characterize the transition region with the theoretical model.....	30
D.2.9 Step 7: compute the cut-off wavelength, λ_C	31
D.3 Fibre deployment method for artifact attenuation	32
Bibliography.....	34
List of comments.....	35
Figure 1 – Cut-off measurement system block diagram.....	9
Figure 2 – Deployment configuration for cable cut-off wavelength λ_{CC} , method A.....	11
Figure 3 – Deployment configuration for cable cut-off wavelength λ_{CC} , method B.....	12
Figure 3 – Default configuration to measure λ_C.....	
Figure 4 – Deployment configurations for fibre cut-off measurement.....	
Figure 4 – Standard deployment for fibre cut-off wavelength measurement	13
Figure 5 – Cut-off wavelength using the bend-reference technique	15
Figure 6 – Cut-off wavelength using the multimode-reference technique	15
Figure 7 – Cable cut-off vs fibre cut-off for a specific fibre (multimode reference).....	21
Figure A.1 – Alternative cable cut-off deployment.....	23
Figure C.1 – Alternative fibre cut-off deployment – Sliding semi-circle.....	25
Figure C.2 – Alternative fibre cut-off deployment – Multi-bend	26
Figure C.3 – Alternative fibre cut-off deployment – Large curve	26
Figure D.1 – Cut-off curve with linear fit error (multimode reference).....	27
Figure D.2 – Fibre cut-off curve fitting technique (multimode reference).....	28
Figure D.3 – Curve fitting regions	28

Figure D.4 – Fibre cut-off curve with artifacts (multimode reference).....	32
Figure D.5 – Fibre cut-off curve with artifacts (bend reference).....	32
Figure D.6 – Fibre deployment with large diameter bends for mode filtering	33
Figure D.7 – Fibre cut-off curve with mode attenuation (multimode reference).....	33

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 1-44: Measurement methods and test procedures – Cut-off wavelength

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This commented version (CMV) of the official standard IEC 60793-1-44:2023 edition 3.0 allows the user to identify the changes made to the previous IEC 60793-1-44:2011 edition 2.0. Furthermore, comments from IEC SC 86A experts are provided to explain the reasons of the most relevant changes, or to clarify any part of the content.

A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text. Experts' comments are identified by a blue-background number. Mouse over a number to display a pop-up note with the comment.

This publication contains the CMV and the official standard. The full list of comments is available at the end of the CMV.

IEC 60793-1-44 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics. It is an International Standard.

This third edition cancels and replaces the second edition published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) used the diameter of the fibre loops to describe deployment;
- b) added Annex D related to cut-off curve artifacts;
- c) reorganized information and added more figures to clarify concepts.

The text of this International Standard is based on the following documents:

Draft	Report on voting
86A/2314/FDIS	86A/2327/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

This document is to be read in conjunction with IEC 60793-1-1.

A list of all parts of the IEC 60793-1 series, published under the general title *Optical fibres – Measurement methods and test procedures*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 1-44: Measurement methods and test procedures – Cut-off wavelength

1 Scope

This part of IEC 60793 establishes uniform requirements for measuring the cut-off wavelength of single-mode optical fibre, thereby assisting in the inspection of fibres and cables for commercial purposes.

This document gives methods for measuring the cut-off wavelength ~~of fibre and cable~~ for uncabled or cabled single mode telecom fibre. These procedures apply to all category B and C fibre types.

~~There are two methods for measuring cable cut-off wavelength, λ_{cc} :~~

- ~~• Method A: using uncabled fibre;~~
- ~~• Method B: using cabled fibre.~~

~~There is only one method (Method C) for measuring fibre cut-off wavelength, λ_c .~~

~~The test method in this standard describes procedures for determining the cut-off wavelength of a sample fibre in either an uncabled condition (λ_c) or in a cable (λ_{cc}). Three default configurations are given here: any different configuration will be given in a detail specification. These procedures apply to all category B and C fibre types (see Normative references).~~

There are three methods of deployment for measuring the cut-off wavelength:

- method A: cable cut-off using uncabled fibre 22 m long sample, λ_{cc} ;
- method B: cable cut-off using cabled fibre 22 m long sample, λ_{cc} ;
- method C: fibre cut-off using uncabled fibre 2 m long sample, λ_c .

All methods require a reference measurement. There are two reference-scan techniques, either or both of which ~~may~~ can be used with all methods:

- bend-reference technique;
- multimode-reference technique using category A1(OM1-OM5) multimode fibre.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-1, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*

~~IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*~~

INTERNATIONAL STANDARD



**Optical fibres –
Part 1-44: Measurement methods and test procedures – Cut-off wavelength**



CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Background	7
5 Overview of methods	7
6 Reference test method	8
7 Apparatus	8
7.1 Light source	8
7.2 Modulation	8
7.3 Launch optics	8
7.4 Support and positioning apparatus	8
7.5 Deployment mandrel	9
7.5.1 General	9
7.5.2 Cable cut-off wavelength deployment, method A	9
7.5.3 Cable cut-off wavelength deployment, method B	9
7.5.4 Fibre cut-off wavelength deployment, method C	9
7.6 Detection optics	10
7.7 Detector assembly and signal detection electronics	10
7.8 Cladding mode stripper	10
8 Sampling specimen	10
8.1 Specimen length	10
8.2 Specimen end face	10
9 Procedure	11
9.1 Positioning of specimen in apparatus	11
9.1.1 General requirements for all methods	11
9.1.2 Deployment requirements for each method	11
9.2 Measurement of output power	11
9.2.1 Overview	11
9.2.2 Bend-reference technique	12
9.2.3 Multimode-reference technique	12
10 Calculations	12
10.1 Bend-reference technique	12
10.2 Multimode-reference technique	13
11 Mapping functions	14
12 Results	14
13 Specification information	15
Annex A (normative) Requirements specific to method A – Cable cut-off wavelength, λ_{CC} , using uncabled fibre	16
A.1 Specimen length	16
A.2 Procedure – Position specimen on deployment mandrel	16
Annex B (normative) Requirements specific to method B – Cable cut-off wavelength, λ_{CC} , using cabled fibre	17
B.1 Specimen length	17
B.2 Procedure – Position specimen on deployment mandrel	17

Annex C (normative) Requirements specific to method C – Fibre cut-off wavelength, λ_C	18
C.1 Specimen length	18
C.2 Procedure – Position specimen on deployment mandrel.....	18
Annex D (informative) Cut-off curve artifacts.....	20
D.1 Description of curve artifacts.....	20
D.2 Curve-fitting technique for artifact filtering.....	20
D.2.1 Overview	20
D.2.2 General	21
D.2.3 Step 1: define the upper wavelength region	22
D.2.4 Step 2: characterize the spectral transmittance	22
D.2.5 Step 3: calculate the deviation of the spectral transmittance from the linear fit	22
D.2.6 Step 4: determine the end wavelength of the transition region	23
D.2.7 Step 5: determine the start wavelength of the transition region	23
D.2.8 Step 6: characterize the transition region with the theoretical model	23
D.2.9 Step 7: compute the cut-off wavelength, λ_C	24
D.3 Fibre deployment method for artifact attenuation	25
Bibliography.....	27
Figure 1 – Cut-off measurement system block diagram	7
Figure 2 – Deployment configuration for cable cut-off wavelength λ_{CC} , method A.....	9
Figure 3 – Deployment configuration for cable cut-off wavelength λ_{CC} , method B.....	9
Figure 4 – Standard deployment for fibre cut-off wavelength measurement.....	10
Figure 5 – Cut-off wavelength using the bend-reference technique	11
Figure 6 – Cut-off wavelength using the multimode-reference technique	12
Figure 7 – Cable cut-off vs fibre cut-off for a specific fibre (multimode reference)	14
Figure A.1 – Alternative cable cut-off deployment	16
Figure C.1 – Alternative fibre cut-off deployment – Sliding semi-circle	18
Figure C.2 – Alternative fibre cut-off deployment – Multi-bend	19
Figure C.3 – Alternative fibre cut-off deployment – Large curve	19
Figure D.1 – Cut-off curve with linear fit error (multimode reference)	20
Figure D.2 – Fibre cut-off curve fitting technique (multimode reference).....	21
Figure D.3 – Curve fitting regions	21
Figure D.4 – Fibre cut-off curve with artifacts (multimode reference).....	25
Figure D.5 – Fibre cut-off curve with artifacts (bend reference).....	25
Figure D.6 – Fibre deployment with large diameter bends for mode filtering.....	26
Figure D.7 – Fibre cut-off curve with mode attenuation (multimode reference)	26

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 1-44: Measurement methods and test procedures – Cut-off wavelength

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60793-1-44 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics. It is an International Standard.

This third edition cancels and replaces the second edition published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) used the diameter of the fibre loops to describe deployment;
- b) added Annex D related to cut-off curve artifacts;
- c) reorganized information and added more figures to clarify concepts.

The text of this International Standard is based on the following documents:

Draft	Report on voting
86A/2314/FDIS	86A/2327/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

This document is to be read in conjunction with IEC 60793-1-1.

A list of all parts of the IEC 60793-1 series, published under the general title *Optical fibres – Measurement methods and test procedures*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 1-44: Measurement methods and test procedures – Cut-off wavelength

1 Scope

This part of IEC 60793 establishes uniform requirements for measuring the cut-off wavelength of single-mode optical fibre, thereby assisting in the inspection of fibres and cables for commercial purposes.

This document gives methods for measuring the cut-off wavelength for uncabled or cabled single mode telecom fibre. These procedures apply to all category B and C fibre types.

There are three methods of deployment for measuring the cut-off wavelength:

- method A: cable cut-off using uncabled fibre 22 m long sample, λ_{CC} ;
- method B: cable cut-off using cabled fibre 22 m long sample, λ_{CC} ;
- method C: fibre cut-off using uncabled fibre 2 m long sample, λ_c .

All methods require a reference measurement. There are two reference-scan techniques, either or both of which can be used with all methods:

- bend-reference technique;
- multimode-reference technique using category A1(OM1-OM5) multimode fibre.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-1, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*