



# INTERNATIONAL STANDARD

---

**Materials for printed boards and other interconnecting structures –  
Part 2-47: Reinforced base materials clad and unclad – Non-halogenated  
epoxide non-woven/woven E-glass reinforced laminate sheets of thermal  
conductivity 2,0 W/(m•K) and defined flammability (vertical burning test),  
copper-clad for lead-free assembly**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

---

ICS 31.180

ISBN 978-2-8322-5198-0

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions.....	6
4 Materials and construction .....	7
4.1 General.....	7
4.2 Resin system .....	7
4.3 Metal foil.....	7
4.4 Reinforcement.....	7
5 Electrical properties .....	7
6 Non-electrical properties of the copper-clad laminate .....	8
6.1 Appearance of the copper-clad sheet.....	8
6.1.1 General .....	8
6.1.2 Indentations (pits and dents).....	8
6.1.3 Wrinkles .....	8
6.1.4 Scratches .....	8
6.1.5 Raised areas .....	9
6.2 Appearance of the unclad face .....	9
6.3 Laminate thickness .....	9
6.4 Bow and twist.....	9
6.5 Properties related to the copper foil bond .....	10
6.6 Punching and machining .....	11
6.7 Dimensional stability.....	11
6.8 Sheet sizes .....	11
6.8.1 Typical sheet sizes.....	11
6.8.2 Tolerances for sheet sizes .....	11
6.9 Cut panels.....	12
6.9.1 Cut panel sizes .....	12
6.9.2 Size tolerances for cut panels .....	12
6.9.3 Rectangularity of cut panels .....	12
6.10 Thermal conductivity .....	12
7 Non-electrical properties of the base material after complete removal of the copper foil.....	13
7.1 Appearance of the dielectric base material .....	13
7.2 Flexural strength .....	13
7.3 Flammability.....	13
7.4 Water absorption.....	14
7.5 Measling .....	14
7.6 Glass transition temperature and cure factor .....	14
7.7 Decomposition temperature.....	15
7.8 Time to delamination (TMA) .....	15
7.9 Halogen content .....	15
8 Quality assurance .....	15
8.1 Quality system .....	15
8.2 Responsibility for inspection .....	16
8.3 Qualification inspection .....	16
8.4 Quality conformance inspection .....	16

8.5	Certificate of conformance .....	16
8.6	Safety data sheet .....	16
9	Packaging and marking.....	16
10	Ordering information .....	17
Annex A (informative)	Engineering information .....	18
A.1	General.....	18
A.2	Chemical properties .....	18
A.3	Electrical properties .....	18
A.4	Flammability properties .....	18
A.5	Mechanical properties .....	18
A.6	Physical properties.....	18
A.7	Thermal properties .....	18
Annex B (informative)	Common laminate constructions.....	20
Annex C (informative)	Guideline for qualification and conformance inspection.....	21
Bibliography	.....	22
Table 1	– Electrical properties .....	7
Table 2	– Size of indentations .....	8
Table 3	– Nominal thickness and tolerance of metal-clad laminate .....	9
Table 4	– Bow and twist requirements .....	10
Table 5	– Pull-off and peel strength requirements .....	10
Table 6	– Dimensional stability .....	11
Table 7	– Size tolerances for cut panels .....	12
Table 8	– Rectangularity of cut panels .....	12
Table 9	– Thermal conductivity.....	12
Table 10	– Flexural strength requirements .....	13
Table 11	– Flammability requirements .....	14
Table 12	– Water absorption requirements .....	14
Table 13	– Measling requirements .....	14
Table 14	– Glass transition temperature and cure factor requirements .....	15
Table 15	– Decomposition temperature requirements .....	15
Table 16	– Time to delamination requirements.....	15
Table 17	– Halogen content.....	15
Table C.1	– Qualification and conformance inspection .....	21

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

### MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

#### **Part 2-47: Reinforced base materials clad and unclad – Non-halogenated epoxide non-woven/woven E-glass reinforced laminate sheets of thermal conductivity 2,0 W/(m•K) and defined flammability (vertical burning test), copper-clad for lead-free assembly**

#### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61249-2-45 has been prepared by IEC technical committee 91: Electronics assembly technology.

The text of this International Standard is based on the following documents:

CDV	Report on voting
91/1449/FDIS	91/1485/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61249 series, under the general title *Materials for printed boards and other interconnecting structures*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

## MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

### **Part 2-47: Reinforced base materials clad and unclad – Non-halogenated epoxide non-woven/woven E-glass reinforced laminate sheets of thermal conductivity 2,0 W/(m•K) and defined flammability (vertical burning test), copper-clad for lead-free assembly**

#### **1 Scope**

This part of IEC 61249 gives requirements for properties of non-halogenated epoxide non-woven reinforced core/woven E-glass reinforced surface laminate sheets of thermal conductivity and defined flammability (vertical burning test), copper-clad for lead-free assembly in thicknesses of 0,60 mm up to 1,70 mm. The flammability rating is achieved through the use of non-halogenated fire retardants reacted as part of the epoxide polymeric structure. The glass transition temperature is defined to be 105 °C minimum. Thermal conductivity is defined to be  $(2,0 \pm 0,30)$  W/(m•K).

#### **2 Normative references**

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2:2006, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 2: Test methods for materials for interconnection structures*

IEC 61249-5-1, *Materials for interconnection structures – Part 5: Sectional specification set for conductive foils and films with and without coatings – Section 1: Copper foils (for the manufacture of copper-clad base materials)*

IEC/PAS 61249-6-3, *Specification for finished fabric woven from "E" glass for printed boards*

ISO 11014, *Safety data sheet for chemical products – Content and order of sections*