

IEC 62899-202

Edition 2.0 2023-05

INTERNATIONAL STANDARD

Printed electronics – Part 202: Materials – Conductive ink

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 31.180; 87.080

ISBN 978-2-8322-6936-7

Warning! Make sure that you obtained this publication from an authorized distributor.

– 2 –

IEC 62899-202:2023 © IEC 2023

CONTENTS

FC	FOREWORD					
IN	INTRODUCTION					
1	Scop	e	7			
2	Norm	ative references	7			
3	3 Terms and definitions					
4	Atmospheric conditions for evaluation and pre-conditioning					
5	Summary characteristics and evaluation method of conductive ink					
6	Evalı	lation of properties of conductive ink	12			
U	6 1	Snecimen	12			
	6.2	Contents	12			
	621	Solid content				
	6.2.2	Non-volatile content				
	6.2.3	Ash content				
	6.2.4	Foreign matter	13			
	6.3	Physical properties	14			
	6.3.1	Density	14			
	6.3.2	Rheology	14			
	6.3.3	Surface tension	15			
	6.3.4	Size of conductive materials	16			
	6.3.5	Flashpoint	17			
	6.3.6	Evaporation rate	18			
	6.3.7	Appearance of ink	19			
7	7 Evaluation of the properties of a conductive layer					
	7.1	Test piece	19			
	7.1.1	General	19			
	7.1.2	Substrate	19			
	7.1.3	Conductive ink	19			
	7.1.4	Dimensions of test piece	19			
	7.1.5	Preparation of test piece				
	7.2	Electrical properties	20			
	7.2.1	Volume resistivity	20			
	7.2.2	Surface resistivity (based on the four-point probe method)				
	7.2.3	Surface resistivity (based on the contactless method)				
	1.3	Bonding tost				
	732	Abrasion resistance	25			
	733	Adhesion strength	20			
	7 4	Ontical properties	27			
	7.4.1	Overview	27			
	7.4.2	Luminous transmittance				
	7.4.3	Chromaticity				
	7.4.4	Uniformity of colour				
	7.4.5	- Haze				
	7.4.6	Refractive index				
8	Stora	ge	31			
	8.1	Storage conditions	31			

8.2	Method for measuring aged deterioration	.31			
8.3	Report of the results	.31			
Annex A (informative) Example of four-point probe for applying an appropriate weight32					
A.1	Internal structure	.32			
A.2	Example of overall view	.32			
Annex B (informative) Formula of correction factor F					
B.1	General	.33			
B.2	Conditions for correction factor F	.34			
B.3	Formula of correction factor F	.34			
Annex C (informative) Influence of the measuring position and size of the specimen on resistance					
C.1	Influence of the measuring position on resistance	.35			
C.2	Influence of the size of the specimen on resistance	.36			
Bibliograp	bhy	.37			
Figure 1 -	- Example of four-point probe measurement	.20			
Figure 2 – Example of four-probe measurement equipment					
Figure 3 -	- Measuring positions of resistance (Type A)	.22			
Figure 4 – Measuring positions of resistance (Type B)2					
Figure 5 – Measuring positions of resistance (Type C)					
Figure A.1 – Example of the internal structure of probe					
Figure A.2 – Example of the overall view of the probe					
Figure B.1 – Schematic diagram of the geometry of the conductive layer and the configuration of probes A, B, C and D					
Figure C.1 – Measurement model for the influence of the measuring position on sheet resistance					
Figure C.	2 – Model measurement of the influence of the specimen size	.36			
Table 1 – Test methods for conductive inks used in PE1					
Table 2 – Resistance range of the test piece and the applied current					
Table 3 – List of the size of the specimen					

This is a preview - click here to buy the full publication

- 4 -

IEC 62899-202:2023 © IEC 2023

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRINTED ELECTRONICS –

Part 202: Materials – Conductive ink

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 62899-202 has been prepared by IEC technical committee 119: Printed electronics. It is an International Standard.

This second edition cancels and replaces the first edition published in 2016. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) definitions of conductive material, conductive ink and conductive layer have been revised;
- b) a summary of test methods is added;
- c) mechanical tests for conductive layer are added.

– 5 –

The text of this International Standard is based on the following documents:

Draft	Report on voting
119/423/FDIS	119/428/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 62899 series, published under the general title *Printed electronics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

- 6 -

IEC 62899-202:2023 © IEC 2023

INTRODUCTION

Printed electronics is a technology that spans the printing and electrical/electronic area, and it provides a variety of products. Since participants in this industry come from different areas, their backgrounds and customs can be barriers to smooth communication and transactions in the supply chain. The printed electronics industry continues to grow, but many barriers still remain. Particularly, the lack of standardised terms and evaluation methods is one of the major factors that inhibit smooth communication.

This document focuses on measurement and evaluation methods for conductive inks and provides tools to promote the smooth communication within the supply chain.

This document specifies the basic items to be communicated and their measurement or evaluation methods. This document includes the measurement methods for the basic properties of inks and electrical conductivity, which is obtained by the post treatment of inks. Additionally, storage methods, packaging and marking, and transportation conditions are also included.

This document is part of the IEC 62899-202 series and similar documents are available for other materials used in printed electronics.

The IEC 62899-20x series consists of the following parts:

IEC 62899-201: Materials – Substrates IEC 62899-202: Materials – Conductive ink IEC 62899-203: Materials – Semiconductor ink IEC 62899-204: Materials – Insulator ink

Furthermore, sectional specifications, blank detail specifications, and detail specifications of each material will follow these parts.

-7-

PRINTED ELECTRONICS -

Part 202: Materials – Conductive ink

1 Scope

This part of IEC 62899 defines the terms and specifies the standard test methods for characterization and evaluation of conductive inks.

This document also provides measurement methods for evaluating the properties of conductive layers made both from an additive process using conductive inks and from a subtractive process used in printed electronics.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62899-202-3, Printed electronics – Part 202-3: Materials – Conductive ink – Measurement of sheet resistance of conductive films – Contactless method

IEC 62899-202-5, *Printed electronics – Part 202-5: Materials – Conductive ink – Mechanical bending test of a printed conductive layer on an insulating substrate*

ISO 5-2, Photography and graphic technology – Density measurements – Part 2: Geometric conditions for transmittance density

ISO 5-3, Photography and graphic technology – Density measurements – Part 3: Spectral conditions

ISO 124, Latex, rubber – Determination of total solids content

ISO 291, Plastics – Standard atmospheres for conditioning and testing

ISO 304, Surface active agents – Determination of surface tension by drawing up liquid films

ISO 489:2022, Plastics – Determination of refractive index

ISO 758, Liquid chemical products for industrial use – Determination of density at 20 degrees C

ISO 1183-1, *Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2409:2020, Paints and varnishes – Cross-cut test

ISO 2471, Paper and board – Determination of opacity (paper backing) – Diffuse reflectance method

- 8 -

IEC 62899-202:2023 © IEC 2023

ISO 2555, Plastics – Resins in the liquid state or as emulsions or dispersions – Determination of apparent viscosity using a single cylinder type rotational viscometer method

ISO 2592, Petroleum and related products – Determination of flash and fire points – Cleveland open cup method

ISO 2719, Determination of flash point – Pensky-Martens closed cup method

ISO 2811-1, Paints and varnishes – Determination of density – Part 1: Pycnometer method

ISO 2811-2, Paints and varnishes – Determination of density – Part 2: Immersed body (plummet) method

ISO 2884-1, Paints and varnishes – Determination of viscosity using rotary viscometers – Part 1: Cone-and-plate viscometer operated at a high rate of shear

ISO 3219, Plastics – Polymers/resins in the liquid state or as emulsions or dispersions – Determination of viscosity using a rotational viscometer with defined shear rate

ISO 3251, Paints, varnishes and plastics – Determination of non-volatile-matter content

ISO 3451-1, Plastics – Determination of ash – Part 1: General methods

ISO 3664, Graphic technology and photography – Viewing conditions

ISO 3679, Determination of flash no-flash and flash point – Rapid equilibrium closed cup method

ISO 4576, *Plastics – Polymer dispersions – Determination of sieve residue (gross particle and coagulum content)*

ISO 9276-6, Representation of results of particle size analysis – Part 6: Descriptive and quantitative representation of particle shape and morphology

ISO 11664-4, Colorimetry – Part 4: CIE 1976 L*a*b* colour space

ISO 13319, Determination of particle size distributions – Electrical sensing zone method

ISO 13320, Particle size analysis – Laser diffraction methods

ISO 13321, Particle size analysis – Photon correlation spectroscopy

ISO 13322-1, Particle size analysis – Image analysis methods – Part 1: Static image analysis methods

ISO 13468-1:2019, *Plastics – Determination of the total luminous transmittance of transparent materials – Part 1: Single beam instrument*

ISO 13468-2:2021, *Plastics – Determination of the total luminous transmittance of transparent materials – Part 2: Double-beam instrument*

ISO 13655, Graphic technology – Spectral measurement and colorimetric computation for graphic arts images

- 9 -

ISO 14488, Particulate materials – Sampling and sample splitting for the determination of particulate properties

ISO 14782, Plastics – Determination of haze for transparent materials

ISO 14887, Sample preparation – Dispersing procedures for powders in liquids

ISO 15212-1, Oscillation-type density meters – Part 1: Laboratory instruments

ISO 18947-1:2021, Imaging materials and prints – Abrasion resistance – Part 1: General rub testing methods

ISO 20379, Fine ceramics (advanced ceramics, advanced technical ceramics) – Measurement of thixotropic behaviour of ceramic slurry by use of a rotational viscometer

ISO 20998-1, Measurement and characterization of particles by acoustic methods – Part 1: Concepts and procedures in ultrasonic attenuation spectroscopy