



INTERNATIONAL STANDARD



**Printed electronics –
Part 503-1: Quality assessment – Test method of displacement current
measurement for printed thin-film transistor**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.045; 31.080.30

ISBN 978-2-8322-8378-3

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Abbreviated terms	7
5 Symbols and units	7
6 Measuring method of DCM	8
6.1 Guidelines on measurements of printed TFT channel properties	8
6.2 Procedure for DCM	8
6.2.1 Measuring apparatus	8
6.2.2 Measuring procedure	8
7 Report	10
7.1 Experimental conditions	10
7.2 Appropriate data format	10
Annex A (informative) Experimental results.....	12
A.1 Charge trapping measurement method	12
A.2 Channel capacitance measurement method	13
Bibliography.....	15
Figure 1 – Example of structure (left) and schema (right) of a measuring device.....	8
Figure 2 – Plots of the printed TFT's U_{GS} , I_S , I_D at $U_{DS} = -20V$ with respect to time	9
Figure 3 – Frequency dependence of DCM	10
Figure A.1 – Plot of DCM at $U_{DS} = 0 V$	13
Figure A.2 – Division of regions according to carrier injection	14
Table 1 – List of symbols	7
Table 2 – Environmental factors.....	11
Table 3 – Measured properties of the TFT	11
Table A.1 – Obtained trap charge from four cycles (accumulated).....	13

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRINTED ELECTRONICS –

**Part 503-1: Quality assessment –
Test method of displacement current
measurement for printed thin-film transistor**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62899-503-1 has been prepared by IEC technical committee 119: Printed Electronics.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
119/303/FDIS	119/307/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62899 series, published under the general title *Printed electronics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

There has been a need for a method to measure and evaluate performance and reliability that is appropriate for printed thin-film transistors (TFTs). In the case of printed TFTs, there is much larger parasitic capacitance than dielectric capacitance in the channel. Accordingly, there has been a need for a method to measure and evaluate the properties for printed TFTs. Carrier behavior is one such property, and mobility and threshold voltage (V_{th}) for TFTs are other properties. In the case of inorganic TFTs, for example complementary metal-oxide semiconductor (CMOS) TFTs, carriers are induced by the strong inversion at the semiconductor/dielectric interface. But in the case of organic or printed TFTs, carrier generation takes place in the accumulation mode. The total number of carriers in the organic semiconductor layer can often be insufficient to enrich the carrier concentration at the channel. There exists a carrier injection. The carrier injection occurs at the interface of the organic semiconductors' source/drain electrodes. There are three methods to investigate the carrier injection property, that is, Kelvin probe microscopy, four-terminal measurement, and displacement current measurement (DCM). Both Kelvin probe microscopy and four-terminal measurement are indirect methods, but DCM is a direct method to detect charge motion in semiconductors, molecular thin films, and nanoparticles. In this document, the DCM-based channel charge trapping and channel capacitance measurement method is proposed as a measuring method for the carrier properties of organic or printed TFTs.

PRINTED ELECTRONICS –

Part 503-1: Quality assessment – Test method of displacement current measurement for printed thin-film transistor

1 Scope

This part of IEC 62899 specifies a test method for displacement current measurement (DCM) for printed thin-film transistors (TFTs) or organic thin-film transistors (OTFTs).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics – Standard atmospheres for conditioning and testing*