

This is a preview - click here to buy the full publication



IEC TR 63307

Edition 1.0 2020-11

TECHNICAL REPORT



Measurement methods of the complex relative permeability and permittivity of noise suppression sheet

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.100.10

ISBN 978-2-8322-9085-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	6
INTRODUCTION.....	8
1 Scope.....	9
2 Normative references	9
3 Terms, definitions and symbols.....	9
3.1 Terms and definitions.....	9
3.2 Symbols.....	9
4 General	10
5 Measurement methods	11
5.1 Inductance method	11
5.1.1 Measurement parameters	11
5.1.2 Measurement frequency and accuracy.....	11
5.1.3 Measurement principle.....	12
5.1.4 Test sample.....	14
5.1.5 Test fixture	14
5.1.6 Measurement environment.....	14
5.1.7 Measurement uncertainty.....	14
5.1.8 Measurement system.....	16
5.1.9 Measurement procedure	16
5.1.10 Example of measurement results	16
5.1.11 Remarks	17
5.2 Nicolson Ross Weir method	18
5.2.1 Principle	18
5.2.2 Measurement frequency and accuracy.....	20
5.2.3 Measurement parameters	20
5.2.4 Test sample.....	20
5.2.5 Measurement environment.....	21
5.2.6 Measurement uncertainty.....	21
5.2.7 Measurement system.....	22
5.2.8 Test fixture	22
5.2.9 Measurement procedure	22
5.2.10 Example of measurement results	23
5.2.11 Remarks	23
5.3 Short-circuited microstrip line method	24
5.3.1 Principle	24
5.3.2 Measurement frequency and accuracy.....	25
5.3.3 Measurement parameters	25
5.3.4 Test sample.....	25
5.3.5 Measurement environment.....	26
5.3.6 Measurement system.....	26
5.3.7 Test fixture (MSL jig)	26
5.3.8 Measurement procedure	27
5.3.9 Results (example).....	27
5.3.10 Remarks	28
5.4 Short-circuited coaxial line method	28
5.4.1 Principle	28

5.4.2	Measurement frequency and accuracy	29
5.4.3	Measurement parameters	30
5.4.4	Test sample	30
5.4.5	Measurement environments	30
5.4.6	Measurement system	30
5.4.7	Test fixture (coax jig)	31
5.4.8	Measurement procedure	31
5.4.9	Results (example)	32
5.4.10	Remarks	33
5.5	Shielded loop coil method	33
5.5.1	Measurement principle	33
5.5.2	Measurement frequency and accuracy	38
5.5.3	Measurement parameters	39
5.5.4	NSS sample dimension and recommendation	39
5.5.5	Measurement environment	40
5.5.6	Measurement system	40
5.5.7	Measurement procedure	40
5.5.8	Measurement results	41
5.5.9	Summary	44
5.6	Harmonic resonance cavity perturbation method	45
5.6.1	Theory	45
5.6.2	Permeability evaluation	46
5.6.3	Permittivity evaluation	53
Annex A (informative) Derivation of the complex relative permeability of the inductance method		59
Annex B (informative) Short-circuited microstrip line method		61
B.1	Fundamental calculation	61
B.2	Determination of C_S and G_S	62
B.3	Determination of demagnetization factor N and coupling coefficient η	64
B.4	Analysis with the software to determine the μ_r	64
Annex C (informative) Short-circuited coaxial line method		66
C.1	Fundamental calculation to determine μ_r	66
C.2	Open-circuited coaxial line	67
C.2.1	Measurement of effective permittivity $\varepsilon_r (\varepsilon'_r - j\varepsilon''_r)$	67
C.2.2	Example of the complex permittivity	70
C.3	Remarks on lumped element approximation	71
Bibliography		73
Figure 1 – In-plane and perpendicular measurement direction of NSS sample		11
Figure 2 – Toroidal-shaped sample cut from the NSS		12
Figure 3 – Test fixture with a toroidal-shaped NSS sample		13
Figure 4 – Equivalent circuit model of the test fixture		13
Figure 5 – Schematic diagram of measurement system		16
Figure 6 – Measurement results of NSS samples		17
Figure 7 – Schematic diagram of a test fixture with a sample and signal flow graph		18
Figure 8 – Cross section of coaxial line with NSS		20
Figure 9 – Dimensions of test sample		21

Figure 10 – Schematic diagram of equipment system for measurement	22
Figure 11 – Specification for test fixture of a 7 mm coaxial transmission line	22
Figure 12 – Measurement results of noise suppression sheet	23
Figure 13 – Equivalent circuits for the MSL	25
Figure 14 – Rectangular shape of NSS sample	26
Figure 15 – Measurement system	26
Figure 16 – Short-circuited microstrip line test fixture (MSL jig).....	27
Figure 17 – Complex relative permeability of a NSS sample C with 0,236 mm thickness, as measured at $N = 0$ (and $\eta = 0,135 2$) and corrected by demagnetization factor $N = 0,037$ (and $\eta = 0,135 2$)	28
Figure 18 – Equivalent circuits for the coax jig	29
Figure 19 – Toroidal shape of NSS sample	30
Figure 20 – Measurement system	31
Figure 21 – Short-circuited coaxial line test fixture (coax jig).....	31
Figure 22 – Complex relative permeability of a NSS sample A with 0,29 mm thickness, as measured and corrected by the permittivity	32
Figure 23 – Complex relative permeability of a NSS sample B with 0,25 mm thickness, as measured and corrected by the effective permittivity	33
Figure 24 – Structure of shielded loop coil	34
Figure 25 – Shielded loop coil and NSS sample arrangement	34
Figure 26 – Whole structure of the measuring unit of the equipment	35
Figure 27 – DC magnetization curve	38
Figure 28 – Estimation of absolute value correction coefficient M'_s	38
Figure 29 – Recommended shape of NSS sample.....	39
Figure 30 – Block diagram of measurement system	40
Figure 31 – Measured complex relative permeability as a function of the size of a NSS sheet (Sample A-01)	42
Figure 32 – Measured complex relative permeability as a function of the size of a NSS sheet (Sample B-01)	43
Figure 33 – Measured complex relative permeability of a NSS sheet as a function of DC bias field intensity (Sample A-02).....	43
Figure 34 – Measured complex relative permeability after absolute value calibration (Sample A-01)	44
Figure 35 – Measured complex relative permeability after absolute value calibration (Sample B-01)	44
Figure 36 – Electromagnetic flux to evaluate permeability in the harmonic resonance cavity resonator	47
Figure 37 – Example of the resonance characteristics change	47
Figure 38 – Cavity resonator for 3,6 GHz to 7,2 GHz	48
Figure 39 – Cavity resonator for 0,25 GHz to 2 GHz	48
Figure 40 – Examples of resonance frequencies	49
Figure 41 – Example of the resonance curves of a harmonic resonance cavity	49
Figure 42 – Examples of samples	50
Figure 43 – Measuring system	50
Figure 44 – Sample installation in the cavity for the permeability measurement	51
Figure 45 – Measured results of the permeability for Sample A and B and a copper rod	53

Figure 46 – Electromagnetic flux to evaluate permittivity in the harmonic resonance cavity resonator	53
Figure 47 – Sample installation in the cavity for the permittivity measurement	55
Figure 48 – Adjustment procedure and adjusted results	56
Figure 49 – Measured results of the permittivity for the two samples, A and B	58
Figure B.1 – Complex relative permeabilities of Sample C with 0,236 mm thickness for toroidal shape and rectangular shape corrected by $N = 0,037$ and $\eta = 0,135 2$	64
Figure B.2 – Complex relative permeabilities of Sample C with 0,236 mm thickness for rectangular shape corrected by $N = 0, 0,018 5$ and $0,037$ with $\eta = 0,135 2$	65
Figure B.3 – Complex relative permeabilities of Sample C with 0,236 mm thickness for rectangular shape corrected by $\eta = 0,225 3, 0,169$ and $0,135 2$ with $N = 0,037$	65
Figure C.1 – Open-circuited coaxial line jig	68
Figure C.2 – Equivalent circuits for the open-circuited coaxial line	68
Figure C.3 – Complex relative permittivity of NSS Sample A with 0,29 mm thickness, as measured and corrected by the permeability	71
Figure C.4 – Complex relative permittivity of NSS Sample B with 0,25 mm thickness, as measured and corrected by the permeability	71
Figure C.5 – Dependence of phase shift βt on frequency	72
Table 1 – Measurement method and frequency	10
Table 2 – Measurement sample table	42

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MEASUREMENT METHODS OF THE COMPLEX RELATIVE PERMEABILITY AND PERMITTIVITY OF NOISE SUPPRESSION SHEET

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC TR 63307, which is a technical report, has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

The text of this Technical Specification is based on the following documents:

Draft TR	Report on voting
51/1349/DTR	51/1356/RVDTR

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Report is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Noise suppression sheet (NSS) is used near the source of high frequency electromagnetic noise, path of noise propagation and source of emission. It is used like a patch and is different from an electromagnetic wave absorber in free space. IEC 62333-2 specifies five measurement methods in order to estimate the effect of NSS. To evaluate the effect by computer simulation, it is indispensable to know the frequency characteristics of both permeability and permittivity. And to make a rough estimate of the noise suppression effect of NSS, it is useful to understand effective permeability and effective permittivity, which are the permeability and permittivity of an actually used shape.

As most NSSs are flexible, and both complex relative permeability and complex relative permittivity have anisotropy, careful study and understanding of the principles are indispensable for the measurement of the frequency characteristics of permeability and permittivity.

There are various methods to measure permeability and permittivity under the frequency range where NSS is used. This document is intended to be used for the proper selection of the measurement method and the preparation of the test sample to achieve the above purpose when measuring permeability and permittivity, the two parameters which largely influence the noise suppression effect of the NSS.

MEASUREMENT METHODS OF THE COMPLEX RELATIVE PERMEABILITY AND PERMITTIVITY OF NOISE SUPPRESSION SHEET

1 Scope

This document provides guidelines on the methods for measuring the frequency characteristics of permeability and permittivity in the frequency range of 1 MHz to 6 GHz for a noise suppression sheet for each electromagnetic noise countermeasure.

2 Normative references

There are no normative references in this document.